

Analytical Reference Materials International

Certificate of Analysis Certified Reference Material



Grade: **Alloy 925, UNS N09925**

Part Number (Q.A. NO.): **IARM 275A**

Certificate Date: **02/12/2008**

Certificate No.: **275A-02122008-IARM-F**

Revision Date: **02/12/2008**

Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a **parentheses ()** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets []** indicates **further testing is in process**.
4. The **"±Estimated Uncertainty"** is enclosed by a **parentheses ()** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Aluminum</u>	<u>Boron</u>	<u>Carbon</u>	<u>Cobalt</u>	<u>Chromium</u>	<u>Copper</u>	<u>Iron</u>	<u>Lead</u>
0.22 (0.01)	0.002 (0.0004)	0.010 (0.001)	0.41 (0.01)	20.1 (0.1)	1.77 (0.02)	27.9 (0.1)	
<u>Magnesium</u>	<u>Manganese</u>	<u>Molybdenum</u>	<u>Nitrogen</u>	<u>Niobium</u>	<u>Nickel</u>	<u>Oxygen</u>	<u>Phosphorus</u>
<0.001	0.61 (0.01)	3.20 (0.03)	0.0033 (0.0003)	0.27 (0.02)	42.8 (0.04)	0.0013 (0.0002)	0.019 (0.001)
<u>Silicon</u>	<u>Sulfur</u>	<u>Tantalum</u>	<u>Tin</u>	<u>Titanium</u>	<u>Tungsten</u>	<u>Vanadium</u>	<u>Zirconium</u>
0.23 (0.005)	0.0003 (0.0001)	<0.01	(0.002)	2.31 (0.02)	0.22 (0.01)	0.032 (0.003)	(0.001)

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Anderson Laboratories, Inc. - Greendale, WI
ATI Allvac - Monroe, NC
Cannon Muskegon Corp. - Muskegon, MI
Haynes International, Inc. - Kokomo, IN
Laboratory Testing, Inc. - Hatfield, PA
Massachusetts Materials Research - West Boylston, MA

ATI Allvac - Lockport, NY
Bodycote Testing - Los Angeles, CA
Carpenter Technology Corporation - Reading, PA
Huntington Alloys Corporation - Huntington, WV
Latrobe Specialty Steel Co. - Latrobe, PA
Special Metals IncoTest - Hereford, UK

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs and RMs applicable to the material covered by this certificate are: NIST 345A, 1247, 1763, 1765, IARM 59D, LECO 501-645, IARM 56D, 57A, 59A, LECO 501-550, 501-675, ALPHA AR512, CPI-4000 100074, 1000311, 10M553, NIST 3107, 3131A, 3161A, BS 925, LECO 501-504, 501-643, 501-645, 501-646, 501-674, 501-676, HAS 825B, 925A, BCS 351, 454/1, 462/1, LECO 501-147, 501-551, 502-102, NIST 101G, 131G, BS 925, LECO 501-991, NIST 131G, 1249, 1606, HAS 25-6A, 400M, 400T, 600C, 600T, 805B, 902B, 925A, LECO 501-550, 502-256, NIST 12B, 106B, 123B, 155, 160B, 168, 345, 348A, 349, 349A, 361, 362, 363, 1187, 1208-1, 1320, 1765, 2423, 2424A, LECO 501-550, ALPHA AR892, 2180-H5, 21102Z21, NIST 1198, EURONORM EC155, CRM 196-1, IARM 57B, 59A, 59B, LECO 501-550, 501-674, IARM 27D, BS 825A, ES 0115A, LECO 501-645, NIST 3113, 3114, 3126A, 3132, 3134, 3137, 3155, 3162A, 3163, 3165, IARM 53B, ALPHA AR511, AR512, LECO 501-503, 501-645, NIST 1247, BS 172, 825A, 925, CSN-4, RV 9761, 9762, LECO 501-643, 501-674, EC55, CRM 295-1, NIST 1248, IARM 53B, 57B, 60A, 62B, 64B, 201A, BS 200-1, 263, MBH 11222C

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 02/12/2008.

275A	Al	B	C	Co	Cr	Cu	Fe	Mg	Mn	Mo	N	Nb	Ni	O	P
1	0.250	0.003	0.010	0.40	19.95	1.79	27.82	0.0001	0.60	3.24	0.0029	0.29	42.79	0.0011	0.021
2	0.1992	0.0020	0.0093	0.401	20.199	1.716	27.964	0.0002	0.589	3.188	0.0037	0.283	42.817	0.0018	0.0185
3	0.247	0.0011	0.0098	0.440	20.392	1.723	27.962	0.00075	0.627	3.167	0.00328	0.270	42.740	0.00103	0.0175
4	0.229	0.0023	0.00887	0.412	20.150	1.777	27.85	0.001	0.605	3.166	0.004	0.278	42.80	0.0010	0.0195
5	0.202	0.002	0.013	0.404	20.02	1.804	27.83	0.00023	0.609	3.22	0.0038	0.206	42.72	0.0012	0.018
6	0.215	0.00093	0.0117	0.40	20.03	1.79	27.98	0.0004	0.61	3.18	0.0037	0.282	42.69	0.00114	0.017
7	0.256	0.002	0.011	0.418	20.02	1.77	27.695	0.0005	0.597	3.22	0.0030	0.28	42.720	0.0015	0.019
8	0.212	0.0020	0.0088	0.440	20.14	1.80	27.680	0.0010	0.60	3.20	0.0022	0.27018	42.818	0.0010	0.018
9	0.24	0.00177	0.008	0.392	20.05	1.75	27.9605		0.630	3.144	0.0032	0.31		0.0019	0.0183
10	0.209	0.0014	0.0110	0.3898	20.013	1.763			0.619	3.187	0.0029	0.264		0.00098	0.0194
11	0.214	0.0015	0.0101	0.398	20.194	1.792			0.6064	3.279	0.00334	0.298			0.0208
12	0.2043	0.0008	0.0117	0.4145	19.876	1.799			0.6136			0.2379			0.0200
13	0.218		0.0091		20.2225							0.291			
14	0.2018		0.0073									0.2173			
Mean	0.2212	0.0017	0.0100	0.4091	20.0967	1.7728	27.8602	0.0005	0.6088	3.1992	0.0033	0.2698	42.7619	0.0013	0.0189
STDV.	0.0196	0.0006	0.0016	0.0167	0.1364	0.0297	0.1162	0.0004	0.0121	0.0384	0.0005	0.0299	0.0501	0.0003	0.0013
Certified	0.22	0.002	0.010	0.41	20.1	1.77	27.9	<0.001	0.61	3.20	0.0033	0.27	42.8	0.0013	0.019
95% C.I.	0.01	0.0004	0.001	0.01	0.1	0.02	0.1		0.01	0.03	0.0003	0.02	0.04	0.0002	0.001
Methods	X,A,I,O	I,O	C,O	X,I,O	X,W,I,O	X,I,O	X,W,I,O	A,I,O	X,I,O	X,I,O	F	X,I,O	X,W,I	F	X,W,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

275A	S	Si	Ta	Ti	V	W	Ag	As	Bi	Ca	La	Pb	Sb	Sn	Zr
1	0.0003	0.240	0.001	2.33	0.032	0.23	0.00001	0.009	0.00001	<0.001	<0.0001	0.0016	0.005	0.00137	0.0016
2	0.0003	0.2197	0.001	2.258	0.029	0.197	0.00002	0.0034	<0.00001	0.0002	<0.0005	0.00004	0.0005	0.0010	0.0002
3	0.0002	0.240	0.033	2.311	0.040	0.220	<0.0002	0.0020	<0.0001		<0.0001	0.00003	0.00050	0.0016	0.0010
4	0.00022	0.223	0.0149	2.345	0.025	0.235			0.0024			<0.0005		0.003	0.0016
5	0.0004	0.234	0.00018	2.31	0.027	0.25						<0.001		0.0030	
6	0.0002	0.23	0.0020	2.33	0.025	0.228						<0.0001		0.0026	
7	0.00011	0.240	0.0313	2.31	0.032	0.23						0.0119		0.0045	
8	0.00037	0.23		2.29	0.033	0.215									
9	0.00036	0.242		2.319	0.037	0.213									
10		0.230		2.247	0.0387	0.2066									
11		0.2249		2.310	0.0290	0.211									
12		0.2337		2.387	0.0312	0.2308									
Mean	0.0003	0.2323	0.0119	2.3123	0.0316	0.2222	0.0000	0.0048	0.0012	0.0002	#DIV/0!	0.0034	0.0020	0.0024	0.0011
STDV.	0.0001	0.0073	0.0147	0.0370	0.0050	0.0145	0.0000	0.0037	0.0017	#DIV/0!	#DIV/0!	0.0057	0.0026	0.0012	0.0007
Certified	0.0003	0.23	<0.01	2.31	0.032	0.22								(0.002)	(0.001)
95% C.I.	0.0001	0.005		0.02	0.003	0.01									
Methods	X,C,O	X,I,O	X,I,O	X,I,O	X,I,O	X,I,O								X,H,I,O	X,I

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981- (E) list the following:

Certifying Body: A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.


Reference Material (RM): A material or substance with one or more properties, which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

Methods of Analysis: In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. Each member of the ILAP is furnished a sample pack from a specific location on the batch bar. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.

Certified by: 
 William D. Britt, President/General Manager
 Analytical Reference Materials International

Certificate No.: 275A-02122008-ARM-F
 Certificate Date: 02/12/2008
 Revision Date/No.: 02/12/2008