

# Analytical Reference Materials International

## Certificate of Analysis Certified Reference Material



Grade: **Alloy 800 / UNS N08800**

Part Number (Q.A. NO.): **IARM 58B**

Certificate Date: **09/12/2005**

Certificate No.: **58B-09122005-IARM-F**

Revision Date: **03/11/2009**

### Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a **parentheses ( )** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets [ ]** indicates **further testing is in process**.
4. The **"±Estimated Uncertainty"** is enclosed by a **parentheses ( )** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

**Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!**

<u>Aluminum</u> 0.45 (0.01)	<u>Boron</u> 0.0003 (0.0001)	<u>Carbon</u> 0.073 (0.001)	<u>Cobalt</u> 0.02 (0.005)	<u>Chromium</u> 19.6 (0.1)	<u>Copper</u> 0.011 (0.002)	<u>Iron</u> 47.7 (0.2)	<u>Lead</u> (0.0001)
<u>Magnesium</u> (0.001)	<u>Manganese</u> 0.51 (0.005)	<u>Molybdenum</u> 0.01 (0.003)	<u>Nitrogen</u> 0.010 (0.0005)	<u>Niobium</u> 0.01 (0.002)	<u>Nickel</u> 30.7 (0.1)	<u>Oxygen</u> 0.001 (0.0004)	<u>Phosphorus</u> 0.010 (0.0003)
<u>Silicon</u> 0.282 (0.003)	<u>Sulfur</u> 0.001 (0.0002)	<u>Tantalum</u> <0.01	<u>Tin</u> 0.002 (0.001)	<u>Titanium</u> 0.50 (0.005)	<u>Tungsten</u> 0.01 (0.002)	<u>Vanadium</u> 0.035 (0.001)	<u>Zirconium</u> <0.005

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Anderson Laboratories, Inc. - Greendale, WI  
Carpenter Technology Corporation - Reading, PA  
Kalco Metals, Inc - Farrell, PA  
Latrobe Specialty Steel Co. - Latrobe, PA  
Special Metals IncoTest - Hereford, UK  
The Sulzer Metco (Canada), Inc. - Fort Saskatchewan, AB

Cannon Muskegon Corp. - Muskegon, MI  
Huntington Alloys Corporation - Huntington, WV  
Laboratory Testing, Inc. - Hatfield, PA  
Outokumpu Stainless OY - Tornio Finland  
Stork Herron Testing Laboratories, Inc. - Cleveland, OH  
ThyssenKrupp VDM USA - Florham Park, NJ

**Traceability:** All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs and RMs applicable to the material covered by this certificate are: NIST 73C, 131G, 344, 885, 1246, 1261A, CRM 186B, 187, IARM 58A, NIST 15H, IARM 58A, LECO 501-645, NIST 999, BCS N346, IARM 58A, LECO 501-502, 501-643, 501-675, IARM 58A, BCS351, HAS 800J, BCS 351, 454/1, 462/1, LECO 502-102, 501-551, 501-147, RM R5657, BS 800, ALPHA AR 660, LECO 501-502, 501-551, NIST 131G, 1249, HAS 25-6A, 330B, 400M, 400T, 600C, 600T, 800A, 800K, 805B, 902B, LECO 501-550, 502-256, ALPHA AR 881, IARM 56D, 57C, 59A, 62B, NIST 362, 363, IARM 56A, 58A, BS 86C, IARM 27D, 58A, LECO 501-647, ES0115A, IC76116, IARM 53B, 56B, 57A, LECO 501-503, 501-645, ALPHA AR511, AR512, BS 86C, 86F, LECO 501-502, IARM 58A.

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

**See Reverse Side for Statistical Data and Additional Information Regarding this Material.**

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 03/11/2009.

58B	Al	B	C	Co	Cr	Cu	Fe	Mg	Mn	Mo	N	Nb	Ni	O	P
1	0.4671	0.0005	0.071	0.034	19.64	0.016	47.77	0.00050	0.52	0.001	0.0092	0.0050	30.60	0.0009	0.0093
2	0.442	0.00043	0.0732	0.019	19.619	0.012	48.024	0.0008	0.510	0.017	0.0099	0.009	30.804	0.0004	0.009
3	0.4391	0.0002	0.0711	0.022	19.425	0.014	47.809	0.0009	0.503	0.011	0.01086	0.0123	30.514	0.00104	0.010
4	0.457	0.00007	0.07296	0.016	19.768	0.006	47.70	0.0013	0.529	0.008	0.0095	0.002	30.704	0.0005	0.0096
5	0.445	0.0004	0.0725	0.019	19.540	0.010	47.56	0.0009	0.513	0.007	0.0104	0.0025	30.683	0.0022	0.010
6	0.440	0.00006	0.0725	0.030	19.55	0.0093	47.76	0.0003	0.506	0.010	0.0108	0.009	30.75	0.0016	0.0101
7	0.446	0.0003	0.0732	0.020	19.780	0.013	48.19		0.509	0.0075	0.0099	0.0054	30.640	0.0014	0.0092
8	0.449	0.0002	0.074	0.0224	19.60	0.0082	47.43		0.507	0.011	0.011	0.0041	30.70	0.0014	0.0098
9	0.442		0.074	0.019	19.64	0.013	47.440		0.497	0.0083	0.0084	0.0065	30.93	0.0009	0.0091
10	0.4581		0.0749	0.0095	19.55	0.0075	47.66		0.520	0.0078	0.0098	0.0073	30.65	0.0015	0.0100
11	0.4522		0.0732	0.0378	19.677	0.0106			0.512	0.011	0.0090	0.0095	30.816		0.0105
12			0.0747	0.012	19.677	0.0106			0.512		0.00987	0.0086	30.751		
13				0.0214	19.645				0.515		0.0089		30.701		
14					19.696								30.696		
Mean	0.4489	0.0003	0.0731	0.0217	19.6291	0.0109	47.7343	0.0008	0.5118	0.0091	0.0098	0.0068	30.7099	0.0012	0.0097
STDV.	0.0089	0.0002	0.0012	0.0081	0.0939	0.0029	0.2393	0.0003	0.0082	0.0039	0.0008	0.0031	0.1007	0.0005	0.0005
Certified	0.45	0.0003	0.073	0.02	19.6	0.011	47.7	(0.001)	0.51	0.01	0.010	0.01	30.7	0.001	0.010
95% C.I.	0.01	0.0001	0.001	0.005	0.1	0.002	0.2		0.005	0.003	0.0005	0.002	0.1	0.0004	0.0003
Methods	X,A,I,O	I,O	C,O	X,I,O	X,W,I,O	X,A,I,O	X,I,O	A,I,O	X,I,O	X,A,I,O	F,O	X,I,O	X,I,O	F	X,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

58B	S	Si	Ta	Ti	V	W	Ag	As	Bi	Ca	La	Pb	Sb	Sn	Zr
1	0.0010	0.286	0.01	0.500	0.034	0.0100	0.00001	0.0030	<0.00001	<0.001	<0.0001	0.0001	0.0030	0.0010	0.004
2	0.0009	0.279	0.00003	0.5079	0.035	0.01	0.0001	0.0013	0.00001	0.003		0.000015	0.0003	0.0012	0.00076
3	0.0006	0.283	0.0049	0.494	0.0357	0.009	0.0004	0.0015	<0.001			0.00005	0.00028	0.002	0.0075
4	0.00136	0.288	0.0030	0.513	0.034	0.010		0.0019				0.00005	<0.01	0.00075	0.0016
5	0.0011	0.287	0.0060	0.504	0.033	0.006		0.0028				0.00025	<0.0001	0.003	0.0012
6	0.0007	0.281	0.0095	0.495	0.036	0.0020						0.0003		0.0012	
7	0.001	0.283		0.511	0.034	0.0055								0.0026	
8	0.0007	0.277		0.502	0.0350	0.0092								0.0020	
9	0.0002	0.278		0.497	0.036	0.0045									
10	0.0010	0.2800		0.505	0.0333	0.0115									
11	0.00098			0.510		0.0088									
12	0.0017			0.5162											
13	0.0005			0.488											
14				0.512											
Mean	0.0009	0.2822	0.0056	0.5039	0.0346	0.0079	0.0002	0.0021	0.0000	0.0030		0.0001	0.0012	0.0017	0.0030
STDV.	0.0004	0.0039	0.0038	0.0083	0.0011	0.0029	0.0002	0.0008				0.0001	0.0016	0.0008	0.0028
Certified	0.001	0.282	<0.01	0.50	0.035	0.01		(0.002)				(0.0001)		0.002	<0.005
95% C.I.	0.0002	0.003		0.005	0.001	0.002								0.001	
Methods	X,C,I,O	X,I,O	I,O	X,I,O	X,I,O	X,I,O		H,I,O				H,D,A,I,O		X,H,I,O	X,I

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1992 list the following:

**Certifying Body:** Any technically competent body (organization or firm, public or private) that issues a reference material certificate which provides the information detailed in ISO Guide 31. The only generally accepted certifying body in the United States for primary standards - Standard Reference Materials (SRM) is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD. All other certifying bodies in the United States produce Reference Materials (RM) or Certified Reference Materials (CRM).

**Reference Material (RM):** Material or substance one or more of whose property values are sufficiently homogeneous and well established to be used for the calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

**Certified Reference Material (CRM):** Reference material, accompanied by a certificate, one or more of whose property values are certified by a procedure which establishes its traceability to an accurate realization of the unit in which the property values are expressed, and for which each certified value is accompanied by an uncertainty at a stated level of confidence.


**Inter-Laboratory Analysis Program (ILAP):** Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

**Methods of Analysis:** In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

**Expiration of Certification:** The certification of this IARM is valid indefinitely, within the uncertainty specified, provided the IARM is handled and stored in accordance with the instructions stated on this certificate. The certification is nullified if the IARM is damaged, contaminated, otherwise modified, or used in a manner for which it was not intended.

**Instructions for Use:** The test surface is the side opposite to the labeled surface, which includes the IARM number. The entire thickness of the unit is certified. However, the user is cautioned not to measure disks less than 2 mm thick when using X-ray fluorescence spectrometry. Each packaged disk has been prepared by finishing the test surface using a lathe. The user must determine the correct surface preparation procedure for each analytical technique. The user is cautioned to use care when either resurfacing the disk or performing additional polishing as these processes may contaminate the surface. When not in use, the material should be stored in a cool, dry location. This material was tested using both the solid disks and chips prepared from the disks. The certified values are considered to be representative of the overall average composition of the material.

**Selection of Materials:** A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.

  
 William D. Britt, President, & General Manager  
 Analytical Reference Materials International Corporation

Certificate No.: 58B-09122005-IARM-F  
 Certificate Date: 09/12/2005  
 Revision Date/No.: 03/11/2009