

# Analytical Reference Materials International

## Certificate of Analysis Certified Reference Material



Grade: **AL-6XN / UNS N08367**

Part Number (Q.A. NO.): **IARM 157B**

Certificate Date: **12/18/2006**

Certificate No.: **157B-12182006-IARM-F**

Revision Date: **10/28/2007**

### Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a **parentheses ( )** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets [ ]** indicates **further testing is in process**.
4. The **"±Estimated Uncertainty"** is enclosed by a **parentheses ( )** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

**Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!**

<u>Aluminum</u> 0.015 (0.001)	<u>Boron</u> 0.001 (0.0005)	<u>Carbon</u> 0.014 (0.001)	<u>Cobalt</u> 0.21 (0.01)	<u>Chromium</u> 20.4 (0.04)	<u>Copper</u> 0.21 (0.004)	<u>Iron</u> 48.0 (0.3)	<u>Lead</u>
<u>Magnesium</u>	<u>Manganese</u> 0.40 (0.004)	<u>Molybdenum</u> 6.21 (0.03)	<u>Nitrogen</u> 0.22 (0.003)	<u>Niobium</u> 0.034 (0.002)	<u>Nickel</u> 24.01 (0.04)	<u>Oxygen</u> 0.0025 (0.0003)	<u>Phosphorus</u> 0.022 (0.0005)
<u>Silicon</u> 0.31 (0.005)	<u>Sulfur</u> 0.0005 (0.0001)	<u>Tantalum</u>	<u>Tin</u> 0.006 (0.001)	<u>Titanium</u> 0.005 (0.001)	<u>Tungsten</u> 0.05 (0.01)	<u>Vanadium</u> 0.069 (0.001)	<u>Zirconium</u> <0.005

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Anderson Laboratories, Inc. - Greendale, WI  
ATI Allvac - Monroe, NC  
Carpenter Technology Corporation - Reading, PA  
Laboratory Testing, Inc. - Hatfield, PA  
Lockheed Martin Astronautics - Littleton, CO  
Outokumpu Stainless OY - Tornio Finland

ATI Allvac - Lockport, NY  
Bodycote Materials Testing - Portland, OR  
Deloro Stellite, Inc. - Belleville, ON  
Latrobe Specialty Steel Co. - Latrobe, PA  
MSI Testing & Engineering, Inc. - Melrose Park, IL  
Special Metals IncoTest - Hereford, UK

**Traceability:** All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs and RMs applicable to the material covered by this certificate are: **IARM 157A, BS 189, LECO 501-503, IARM 157A, BS 189, IC19026, ES0115A, LECO 502-072, NIST 348A, 3102A, 3103A, 3107, 3109A, 3128, 3131A, 3155, 3162A, 3161A, 3169, IARM 157A, ALPHA AR881, LECO 501-643, NIST C1154, BS 189, CSN-4, 844153, 875719, RV 717, 718, 719, 720, 721, LECO 501-674, 502-016, ALPHA AR663, IARM 152B, 157A, 162A, JSS 1204-3, BS 81G, 188A, LECO 501-673, 501-987, 502-257, HAS 25-6B, 317B, BCS 351, 454/1, 462/1, 464, LECO 501-551, 502-102, R5657, NIST 1186, IARM 157A, LECO 501-503, 501-553, 502.016, NIST 126C, 3107, RV 717, ECRM 295-1, LECO 501-504, 501-645, 502-072, NIST 1200, 1249, IARM 157A**

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

**See Reverse Side for Statistical Data and Additional Information Regarding this Material.**

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 10/28/2007.

157B	Al	B	C	Co	Cr	Cu	Fe	Mg	Mn	Mo	N	Nb	Ni	O	P
1	0.017	0.0004	0.016	0.210	20.29	0.210	48.37	0.0005	0.40	6.24	0.221	0.030	24.027	0.0027	0.022
2	0.0148	0.0013	0.0142	0.2124	20.4593	0.2092	47.9227	0.0001	0.4024	6.1773	0.2162	0.0367	24.004	0.0025	0.0224
3	0.0132	0.0020	0.0151	0.211	20.388	0.202	47.268	<0.0001	0.400	6.223	0.2160	0.036	24.103	0.0023	0.0211
4	0.0145	0.0013	0.0128	0.212	20.458	0.199	48.50	<0.005	0.399	6.170	0.218	0.0326	23.96	0.0025	0.0202
5	0.0139	0.0008	0.0150	0.2183	20.456	0.2172	47.799	<0.001	0.4008	6.136	0.2206	0.0406	23.978	0.00188	0.0206
6	0.018	0.0003	0.0146	0.208	20.291	0.214	47.71		0.411	6.171	0.2241	0.035	24.06	0.0029	0.0225
7	0.014	0.0010	0.0153	0.219	20.390	0.214	47.8743		0.402	6.212	0.2259	0.0294	24.02	0.0034	0.0211
8	0.012	0.0023	0.0139	0.190	20.34	0.210	48.502		0.39	6.18	0.224	0.033	23.92	0.0021	0.0215
9	0.014	0.0012	0.01377	0.195	20.37	0.194	48.263		0.385	6.23	0.210	0.032	24.039	0.00252	0.0231
10	0.01562	0.0003	0.0137	0.215	20.45	0.205	47.647		0.398	6.18	0.219	0.0400	24.035		0.0213
11	0.018	0.0019	0.01354	0.21739	20.4644	0.21103			0.39529	6.2972	0.222	0.031			0.0211
12	0.0135		0.0157	0.216	20.324	0.208			0.396	6.259	0.21598	0.0311			0.022
13				0.189	20.46				0.3891	6.21	0.2320				0.0211
14				0.1843											
Mean	0.0149	0.0012	0.0145	0.2070	20.3954	0.2078	47.9856	0.0003	0.3976	6.2066	0.2204	0.0340	24.0146	0.0025	0.0215
STDV.	0.0020	0.0007	0.0010	0.0120	0.0674	0.0067	0.4100	0.0003	0.0067	0.0436	0.0055	0.0037	0.0521	0.0004	0.0008
Certified	0.015	0.001	0.014	0.21	20.4	0.21	48.0		0.40	6.21	0.22	0.034	24.01	0.0025	0.022
95% C.I.	0.001	0.0005	0.001	0.01	0.04	0.004	0.3		0.004	0.03	0.003	0.002	0.04	0.0003	0.0005
Methods	X,I,O		C,O	X,I,O	X,W,I,O	X,I,O	X,I,O		X,I,O	X,I,O	F,O	X,I,O	X,O	F	X,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

157B	S	Si	Ta	Ti	V	W	Ag	As	Bi	Ca	La	Pb	Sb	Sn	Zr
1	0.0005	0.300	<0.01	0.0040	0.070	0.040	0.0001	<0.0001	<0.0003	0.00052		<0.0003	0.0051	0.0053	0.0051
2	0.00028	0.3095	0.0224	0.0057	0.0678	0.0423	0.001	0.0090	0.00002	0.0006		<0.0001	0.0015	0.0040	0.0011
3	0.0005	0.326	<0.0001	0.0061	0.070	0.053		0.005		0.0003		0.00004	<0.001	0.0062	0.0010
4	0.0004	0.315	0.002	0.0021	0.0698	0.0452				0.0004		<0.01		0.0054	0.0020
5	0.00051	0.303	<0.001	0.0030	0.0666	0.0495						0.0254		0.0085	0.002
6	0.0006	0.315	0.007	0.0035	0.069	0.045						0.001		0.0079	0.005
7	0.0007	0.314	0.0188	0.0057	0.071	0.045						0.0011		0.0033	
8	0.0005	0.317		0.006	0.071	0.048								0.0061	
9	0.0006	0.307		0.0051	0.068	0.0642								0.008	
10	0.00027	0.305		0.0068	0.069	0.041								0.0045	
11	0.00015	0.308		0.004		0.0676									
12	0.0008	0.3208		0.0049											
Mean	0.0005	0.3117	0.0126	0.0047	0.0692	0.0492	0.0006	0.0070	0.0000	0.0005		0.0069	0.0033	0.0059	0.0027
STDV.	0.0002	0.0076	0.0096	0.0014	0.0014	0.0091	0.0006	0.0028		0.0001		0.0124	0.0025	0.0018	0.0019
Certified	0.0005	0.31		0.005	0.069	0.05								0.006	<0.005
95% C.I.	0.0001	0.005		0.001	0.001	0.01								0.001	
Methods	C,O	X,W,I,O		X,I,O	X,I,O	X,I,O								X,H,I,O	X,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981- (E) list the following:

**Certifying Body:** A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.


**Reference Material (RM):** A material or substance with one or more properties, which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

**Certified Reference Material (CRM):** A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

**Inter-Laboratory Analysis Program (ILAP):** Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

**Methods of Analysis:** In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

**Selection of Materials:** A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. Each member of the ILAP is furnished a sample pack from a specific location on the batch bar. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.

Certified by:   
 William D. Britt, President/General Manager  
 Analytical Reference Materials International

Certificate No.: 157B-12182006-ARM-F  
 Certificate Date: 12/18/2006  
 Revision Date/No.: 10/28/2007