

# Analytical Reference Materials International

## Certificate of Analysis Certified Reference Material



Grade: Alloy 86L20 / UNS NA

Part Number (Q.A. NO.): IARM 182B

Certificate Date: 08/28/2008

Certificate No.: 182B-08282008-IARM-F

Revision Date: 02/26/2009

### Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a parentheses ( ) is a "best estimate" and is NOT CERTIFIED. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in brackets [ ] indicates further testing is in process.
4. The "±Estimated Uncertainty" is enclosed by a parentheses ( ) below the individual element's concentration and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

**Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!**

<u>Aluminum</u> 0.038 (0.001)	<u>Antimony</u> 0.003 (0.001)	<u>Arsenic</u> 0.003 (0.001)	<u>Boron</u> 0.0003 (0.0001)	<u>Calcium</u> (0.0005)	<u>Carbon</u> 0.21 (0.003)	<u>Chromium</u> 0.49 (0.003)	<u>Cobalt</u> 0.006 (0.0004)
<u>Copper</u> 0.017 (0.001)	<u>Lead</u> 0.19 (0.01)	<u>Manganese</u> 0.81 (0.01)	<u>Molybdenum</u> 0.172 (0.002)	<u>Nickel</u> 0.47 (0.003)	<u>Niobium</u> 0.003 (0.001)	<u>Nitrogen</u> 0.0040 (0.0002)	<u>Oxygen</u> 0.003 (0.001)
<u>Phosphorus</u> 0.016 (0.001)	<u>Sulfur</u> 0.037 (0.001)	<u>Silicon</u> 0.27 (0.005)	<u>Tin</u> 0.0019 (0.0002)	<u>Titanium</u> 0.003 (0.001)	<u>Tungsten</u> (0.01)	<u>Vanadium</u> 0.004 (0.0005)	<u>Zirconium</u> 0.001 (0.0003)

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

AK Steel, Middletown Works - Middletown, OH  
Bodycote Testing - Gary, IN  
Bodycote Testing - Portland, OR  
IMR Test Labs - Lansing, NY  
Kalco Metals, Inc - Farrell, PA  
Lockheed Martin Astronautics - Littleton, CO

Anderson Laboratories, Inc. - Greendale, WI  
Bodycote Testing - Los Angeles, CA  
Carpenter Technology Corporation - Reading, PA  
IPSCO Koppel Tubulars - Koppel, PA  
Laboratory Testing, Inc. - Hatfield, PA  
The Timken Company - Canton, OH

**Traceability:** All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs, and RMs applicable to the material covered by this certificate are: NIST 1222, NIST 1763, IARM 182A, 252A, BS 3941, NIST 72F, 293, 361, 3102A, 3103A, 3106, 3107, 3109A, 3113, 3128, 3131A, 3137, 3149, 3155, 3163, 3161A, 3168A, 3169, BS 2-1, LECO 501-643, IARM 32C, 182A, 183A, BS 73A, LECO 501-503, 502-102, NIST 1262, IARM 28H, 252A, BS 61D, 71A, LECO 501-550, BS 61D, 73B, 4931, LECO 501-503, 501-643, IARM 30A, 30B, 35A, 39A, 41A, ALPHA AR873, LECO 501-506, 501-550, NIST 362, 1162, 1763, IARM 27D, 183B, LECO 502-257, ALPHA AR1648, IARM 183A, LECO 501-551, ALPHA AR659, AR872, AR891, NIST 293, 337A, 1160, 1161, 1162, 1163, 1164, 1754, 1760, 1761, 1762, 1763, 1764, 1765, 1766, 1767, BAS 401/1, 402/1, 403/1, 404/1, 405/1, 406/1, 407/1, 408/2, 409/2, 410/2, JSS ST01, ST02, ST03, ST04, ST05, ST06, 172-4, 173-4, 174-4, 175-4, BS 73B, XAAS, XCCV, XCCS, LECO 501-510, 501-645, NIST 361, IARM 32C, BS 72A, 61B

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

**See Reverse Side for Statistical Data and Additional Information Regarding this Material.**

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 02/26/2009.

182B	Al	As	B	C	Co	Cr	Cu	Mn	Mo	N	Nb	Ni	O	P	Pb
1	0.0370	0.0022	0.0003	0.200	0.006	0.490	0.020	0.830	0.170	0.0038	0.0030	0.470	0.00503	0.0150	0.21
2	0.033	0.0036	0.0004	0.212	0.0055	0.490	0.015	0.789	0.165	0.00438	0.004	0.473	0.0048	0.0145	0.235
3	0.0399	0.003	0.0002	0.202	0.0051	0.497	0.0165	0.814	0.171	0.0046	0.0045	0.470	0.0050	0.0163	0.161
4	0.0373	0.0019	0.00017	0.215	0.0061	0.4822	0.0175	0.805	0.174	0.0039	0.0016	0.486	0.0022	0.0149	0.1907
5	0.0388	0.0015	0.0003	0.2008	0.007	0.493	0.0183	0.7822	0.1723	0.00377	0.0027	0.470	0.0044	0.0160	0.205
6	0.0392	0.0032	0.0004	0.199	0.0052	0.499	0.017	0.812	0.170	0.00409	0.0022	0.476	0.00208	0.0160	0.1701
7	0.039	0.0025	0.0006	0.214	0.0058	0.4950	0.014	0.821	0.175	0.0037	0.0035	0.4812	0.0046	0.0165	0.1965
8	0.0370	0.0030	0.00041	0.2121	0.0045	0.490	0.0157	0.8343	0.1772	0.0038	0.0014	0.475	0.0018	0.0154	0.177
9	0.0389		0.00024	0.206	0.0059	0.497	0.017	0.822	0.172	0.00360	0.0020	0.471	0.00171	0.0147	0.193
10	0.0343		0.0001	0.200	0.0061	0.487	0.016	0.801	0.171	0.0045	0.0016	0.470	0.00087	0.0155	0.172
11	0.0385			0.206	0.0064	0.487	0.0158	0.805	0.177	0.00385	0.0022	0.472		0.014	0.204
12	0.035			0.203	0.0053	0.4982	0.014	0.809	0.165	0.0021	0.0021	0.4814		0.0154	0.172
13	0.0394			0.202			0.018	0.8201	0.170		0.0025			0.0173	0.2009
14	0.0377			0.2073			0.0162		0.1719						
Mean	0.0375	0.0026	0.0003	0.2057	0.0057	0.4921	0.0165	0.8111	0.1715	0.0040	0.0026	0.4746	0.0032	0.0155	0.1913
STDV.	0.0021	0.0007	0.0001	0.0056	0.0007	0.0053	0.0017	0.0150	0.0037	0.0003	0.0010	0.0055	0.0016	0.0009	0.0205
Certified	0.038	0.003	0.0003	0.21	0.006	0.49	0.017	0.81	0.172	0.0040	0.003	0.47	0.003	0.016	0.19
95% C.I.	0.001	0.001	0.0001	0.003	0.0004	0.003	0.001	0.01	0.002	0.0002	0.001	0.003	0.001	0.001	0.01
Methods	X,A,I,O	I,O	I,O	C,O	X,I,O	X,A,I,O	X,A,I,O	X,A,I,O	X,A,I,O	F,O	X,I,O	X,A,O	F	X,I,O	X,A,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

182B	S	Si	Sn	Ti	V	W	Bi	Ca	Cd	Mg	Sb	Se	Ta	Zn	Zr
1	0.034	0.270	0.002	0.0030	0.0030	0.006	0.0014	0.0001		<0.0001	0.0029	0.0139	0.0028	0.0020	0.0009
2	0.038	0.270	0.0021	0.001	0.0046	0.0061	0.0009	0.0005		0.0002	0.0029	<0.00003	0.002	0.0034	0.0014
3	0.0385	0.282	0.0018	0.0037	0.0044	0.0024	<0.00003	0.0009			0.0023		0.003	0.0038	0.0015
4	0.0352	0.265	0.0018	0.0035	0.0035	0.0024	<0.00020	0.0004			0.0048		0.0035	0.0009	0.0006
5	0.0381	0.2524	0.0022	0.0030	0.0034	0.011	0.0080				0.0017		0.0034	0.0020	0.0018
6	0.0351	0.271	0.0017	0.005	0.005	0.0022					0.0037				0.0012
7	0.03592	0.268	0.0017	0.0033	0.0032	0.0057									0.0013
8	0.0386	0.2728	0.0022	0.0026	0.0026	0.013									0.0017
9	0.0370	0.273	0.0019	0.0032	0.0029	0.0053									
10	0.0367	0.275		0.0036	0.0038	0.0057									
11	0.0384	0.275		0.0017	0.0045										
12	0.038	0.250		0.0030	0.0034										
13	0.0374	0.267		0.0035	0.0042										
14	0.0380	0.2653													
Mean	0.0371	0.2683	0.0019	0.0031	0.0037	0.0060	0.0034	0.0005	#DIV/0!	0.0002	0.0031	0.0139	0.0029	0.0024	0.0013
STDV.	0.0015	0.0085	0.0002	0.0010	0.0007	0.0036	0.0040	0.0003	#DIV/0!	#DIV/0!	0.0011	#DIV/0!	0.0006	0.0012	0.0004
Certified	0.037	0.27	0.0019	0.003	0.004	(0.01)		(0.0005)			0.003		(0.003)	(0.002)	0.001
95% C.I.	0.001	0.005	0.0002	0.001	0.0005						0.001				0.0003
Methods	X,C,O	X,A,I,O	X,I,O	X,I,O	X,I,O	X,I,O		I,O			X,I,O		X,I,O	I,O	X,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1992 list the following:

**Certifying Body:** Any technically competent body (organization or firm, public or private) that issues a reference material certificate which provides the information detailed in ISO Guide 31. The only generally accepted certifying body in the United States for primary standards - Standard Reference Materials (SRM) is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD. All other certifying bodies in the United States produce Reference Materials (RM) or Certified Reference Materials (CRM).


**Reference Material (RM):** Material or substance one or more of whose property values are sufficiently homogeneous and well established to be used for the calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

**Certified Reference Material (CRM):** Reference material, accompanied by a certificate, one or more of whose property values are certified by a procedure which establishes its traceability to an accurate realization of the unit in which the property values are expressed, and for which each certified value is accompanied by an uncertainty at a stated level of confidence.

**Inter-Laboratory Analysis Program (ILAP):** Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

**Methods of Analysis:** In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

**Selection of Materials:** A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. Each member of the ILAP is furnished a sample pack from a specific location on the batch bar. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.

Certified by:   
 William D. Britt, President/General Manager  
 Analytical Reference Materials International

Certificate No.: 182B-08282008-IARM-F  
 Certificate Date: 08/28/2008  
 Revision Date/No.: 02/26/2009