Analytical Reference Materials International

Certificate of Analysis Certified Reference Material

Grade: Alloy 255 / UNS S32550 Part Number (Q.A. NO.): IARM 239B

Certificate Date: 08/17/2009 Certificate No.: 239B-08172009-IARM-F Revision Date: 08/24/2017

Interpretation of Data

- 1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community.
- 2. Any data reported and enclosed by a parentheses () is a "best estimate" and is NOT CERTIFIED. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
- 3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in brackets [] indicates further testing is in
- 4. The "± Confidence Interval at 95%" is enclosed by a parentheses () below the individual element's concentration.

A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data

Aluminum 0.008 (0.001)	Boron 0.0008 (0.0001)	<u>Carbon</u> 0.013 (0.001)	Cobalt 0.048 (0.001)	Chromium 25.9 (0.1)	<u>Copper</u> 1.48 (0.01)	Manganese 0.86 (0.004)
Molybdenum 3.42 (0.01)	Nitrogen 0.25 (0.01)	Niobium 0.024 (0.003)	Nickel 5.78 (0.02)	Oxygen 0.004 (0.001)	Phosphorus 0.025 (0.0004)	Sulfur 0.0005 (0.0001)
Silicon 0.39 (0.01)	<u>Tin</u> 0.003 (0.001)	<u>Titanium</u> 0.002 (0.0005)	Vanadium 0.099 (0.002)	Tungsten 0.106 (0.003)	Zirconium 0.002 (0.001)	

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Anderson Laboratories, Inc. - Greendale, WI Crucible Specialty Metals - Syracuse, NY Exova - Portland, OR

Huntington Alloys Corporation - Huntington, WV Laboratory Testing, Inc. - Hatfield, PA

MSI Testing & Engineering, Inc. - Melrose Park, IL

ATI Allvac, Lockport - Lockport, NY Deloro Stellite, Inc. - Belleville, ON Exova - Riverside Park, Middlesbrough, UK

Kalco Metals, Inc - Farrell, PA

Latrobe Specialty Steel Co. - Latrobe, PA Special Metals IncoTest - Hereford, UK

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs and RMs applicable to the material covered by this certificate are: IARM 239Å, JSS 1204-3, ALPHA AR1647, HAS 600T, IARM 239A, SYN 255A, OGFB, ALPHA AR881, LECO 501-644, NIST 121D, 160A, LECO 501-503, 502-072, ALPHA AR511, AR660, A3916, ALPHA AR663, AR881, BCS 475, BS 317L, SS 467, ES 287/1, CKD 206, IH RR99/3, LECO 501-644, 502-016, NIST 1763, 1765, IARM 239A, LECO 501-503, 502-072, 502-257, NIST 339, IARM 2C, 4B, 15B, 21B, 239A, LECO 501-551, 501-674, BCS 341, 351, 454/1, 462/1, ES 281, HAS 317B, LECO 501-551, 502-102IARM 212A, 212B, 239A, BS 179, 318, CSN-4, IH RV22, LECO 502-016, IARM 239A.

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 08/24/2017.

239B	Al	В	С	Cr	Со	Cu	Mn	Мо	Ni	Nb	N	0	Р	Se	Si
1	0.0092	0.0007	0.014	25.93	0.0465	1.466	0.86	3.41	5.81	0.0208	0.232	0.0029	0.024	< 0.0001	0.39
2	0.0106	0.0007	0.0132	26.01	0.050	1.470	0.854	3.415	5.77	0.0234	0.251	0.0060	0.0252	0.0016	0.389
3	0.0114	0.0010	0.0122	26.01	0.0504	1.459	0.860	3.415	5.740	0.0302	0.253	0.0043	0.0254	< 0.002	0.378
4	0.0074	0.0009	0.0127	26.113	0.0484	1.476	0.8701	3.405	5.788	0.029	0.2445	0.0033	0.0246	0.00004	0.3835
5	0.0059	0.0005	0.0141	25.853	0.046	1.466	0.857	3.429	5.807	0.0227	0.2515	0.0048	0.0243	0.0006	0.3714
6	0.006	0.0005	0.0115	25.860	0.050	1.476	0.8479	3.430	5.790	0.0241	0.2535	0.0066	0.024	0.00006	0.410
7	0.0083	0.0009	0.0132	25.863	0.0459	1.486	0.854	3.430	5.836	0.024	0.2465	0.0033	0.025		0.4108
8	0.0097	0.0008	0.0116	25.845	0.047	1.483	0.857	3.427	5.768	0.0300	0.2295	0.0041	0.0252		0.385
9	0.006	0.0012	0.0137	25.925	0.046	1.500	0.8634	3.441	5.783	0.018	0.2516	0.0034	0.0253		0.389
10	0.007	0.0009	0.0140	25.753	0.046	1.470	0.864	3.438	5.755	0.025	0.2340	0.00337	0.0252		0.4039
11	0.0077	0.0010	0.0118	26.00	0.0481	1.487	0.860	3.431	5.787	0.0220	0.2584		0.0240		0.398
12		0.0005	0.0120	25.978	0.052	1.477		3.40			0.2410		0.0251		0.388
13			0.0145	25.851				3.432			0.2451				0.3915
14				25.882				3.408							
Mean	0.0081	0.0008	0.0130	25.919	0.0480	1.476	0.8589	3.422	5.785	0.0245	0.2455	0.0042	0.0248	0.0006	0.3914
STDV.	0.0019	0.0002	0.0011	0.094	0.0021	0.011	0.0059	0.013	0.027	0.0039	0.0091	0.0012	0.0006	0.0007	0.0117
Certified	0.008	0.0008	0.013	25.9	0.048	1.48	0.86	3.42	5.78	0.024	0.25	0.004	0.025		0.39
95% C.I.	0.001	0.0001	0.001	0.1	0.001	0.01	0.004	0.01	0.02	0.003	0.01	0.001	0.0004		0.01
Methods	I,O	I,O	C,O	X,W,O	X,I,O	X,I,O	X,I,O	X,I,O	X,W,O	X,I,O	F,O	F	X,I,O		X,W,I,O

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G=GDMS											•				
239B	S	Ta	Sn	Ti	W	٧	Sb	As	Ca	Ce	Н	Pb	Mg	Zn	Zr
1	0.0006	0.0021	0.0020	0.0018	0.1034	0.0941		0.0036	0.0025		0.0003	0.00002	0.0004	0.0094	0.0007
2	0.0006	0.0014	0.0026	0.0029	0.106	0.099		0.0017	0.0010			0.0002	0.0004	0.0071	0.0011
3	0.0001	0.005	0.0004	0.0021	0.108	0.1002		0.0025	0.001			0.001	0.0002	0.0042	0.0029
4	0.0005	0.0023	0.0015	0.0022	0.0970	0.1024		0.004	0.0006			0.00003	0.0002		0.0027
5	0.0007	0.004	0.0035	0.0029	0.098	0.096		0.0049				0.0014			0.0028
6	0.0008	0.008	0.004	0.0015	0.1060	0.1016						0.0001			0.0001
7	0.0003	0.0032	0.0046	0.001	0.110	0.104						0.0021			0.0022
8	0.0004	0.0088	0.0042	0.0026	0.112	0.098									
9	0.0007		0.0026	0.0025	0.107	0.105									
10	0.0004		0.0028	0.0020	0.1076	0.097									
11	0.0006		0.0023			0.0955									
12	0.0005		0.0029												
13	0.0009														
14															
Mean	0.0005	0.0044	0.0028	0.0021	0.1055	0.0993		0.0033	0.0013		0.0003	0.0007	0.0003	0.0069	0.0018
STDV.	0.0002	0.0028	0.0012	0.0006	0.0048	0.0036		0.0013	0.0008			0.0008	0.0001	0.0026	0.0011
Certified	0.0005	(0.004)	0.003	0.002	0.106	0.099		(0.003)	(0.001)			<0.001	(0.0003)	(0.01)	0.002
95% C.I.	0.0001		0.001	0.0005	0.003	0.002									0.001
Methods	C,O	X,I,O	X,H,I,O	X,I,O	X,I,O	X,I,O		X,H,I,O	I,O			H,I,O	H,A,I	H,I	X,I,O

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G=GDMS

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981-(E) list the following:

<u>Certifying Body:</u> A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.

Reference Material (RM): A material or substance with one or more properties which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

<u>Methods of Analysis:</u> In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen and Oxygen are the result of combustion instrument procedures

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length. The majority of materials are in wrought condition. Other methods of manufacture are utilized as a last resort, only in the case of those materials being unavailable in wrought condition. "Batch" samples are taken by removing a one-inch cross section for every thirteen inches of total length from the entire bar. Twenty-five percent of the one inch cross section is converted to chips for analysis by classical wet chemistry, ICP, AA, and combustion procedures and seventy-five percent remains in a solid disk form for OES and X-Ray analysis where applicable. Each member of the ILAP is furnished both a solid sample and the corresponding supply of chips from a specific location on the batch bar. This massive sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data.

Certified by: William Doffice

William D. Britt, President & General Manager Analytical Reference Materials International Certificate No.: 239B-08172009-IARM-F Certificate Date: 04/18/2002

Revision Date/No.: 08/24/2017