

Analytical Reference Materials International

Certificate of Analysis Certified Reference Material



Grade: **Invar 36 / UNS K93601**

Part Number (Q.A. NO.): **IARM 24B**

Certificate Date: **08/09/2007**

Certificate No.: **24B-08092007-IARM-F**

Revision Date: **08/09/2007**

Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a **parentheses ()** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets []** indicates **further testing is in process**.
4. The "**±Estimated Uncertainty**" is enclosed by a **parentheses ()** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Aluminum</u> 0.002 (0.001)	<u>Arsenic</u> <0.005	<u>Boron</u> (0.001)	<u>Carbon</u> 0.053 (0.001)	<u>Cobalt</u> 0.036 (0.002)	<u>Chromium</u> 0.121 (0.002)	<u>Copper</u> 0.052 (0.001)	<u>Iron</u> 62.6 (0.2)
<u>Manganese</u> 0.82 (0.01)	<u>Molybdenum</u> 0.011 (0.001)	<u>Nitrogen</u> 0.0017 (0.0002)	<u>Niobium</u> <0.01	<u>Nickel</u> 35.86 (0.05)	<u>Oxygen</u> 0.003 (0.001)	<u>Phosphorus</u> 0.009 (0.001)	<u>Selenium</u> 0.19 (0.02)
<u>Silicon</u> 0.28 (0.004)	<u>Sulfur</u> 0.0010 (0.0001)	<u>Tantalum</u> <0.005	<u>Tin</u> 0.0018 (0.0003)	<u>Titanium</u> 0.002 (0.001)	<u>Tungsten</u> <0.04	<u>Vanadium</u> <0.005	<u>Zirconium</u> <0.005

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Anderson Laboratories, Inc. - Greendale, WI
Bodycote Materials Testing - Portland, OR
Carpenter Technology Corporation - Reading, PA
Huntington Alloys Corporation - Huntington, WV
Kalco Metals, Inc - Farrell, PA
Outokumpu Stainless OY - Tornio Finland
Special Metals IncoTest - Hereford, UK

ATI Allvac - Lockport, NY
Cannon Muskegon Corp. - Muskegon, MI
Deloro Stellite, Inc. - Belleville, ON
IMR Test Labs - Lansing, NY
Laboratory Testing, Inc. - Hatfield, PA
Precision Rolled Products - Florham Park, NJ

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs and RMs applicable to the material covered by this certificate are: NIST 1158, IARM 4C, ALPHA AR892, LECO 501-502, 501-643, 502-257, 502-269, NIST 131G, 1158, 1159, LECO 501-991IARM 27D, IS 0112A, 0115A, LECO 501-645, NIST 3101A, 3103A, 3106, 3107, 3109A, 3137, 3149, 3155, 3161A, 3162A, 3163, 3168A, 3169, IARM 24A, LECO 501-503, 501-645, ALPHA AR511, AR881, NIST 1158, BS 186, CRM 287, 351, BCS 457-1, HAS 36A, BCS 351, 454/1, 462/1, LECO 501-551, 502-102, R5657, IARM 24A, LECO 501-643, IARM 24D, LECO 501-502, 501-553, BS 186A, ALPHA AR668, LECO 501-502, NIST 899, 1158, BS 186, BCS CRMN 346, LECO 501-502, 501-643, 501-644, 501-992, NIST 131G, HAS 36A, 400M, 805B, LECO 501-550, 502-256, ALPHA AR881, RV9495, RV9498, RV9505, 819435, BS 186, 186A, CSN-4, IARM 24A, CT510, CT686, LECO 501-502, 501-643, 501-644, IARM 24A, LECO 501-643

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 08/09/2007.

24B	Al	B	C	Co	Cr	Cu	Mn	Mo	N	Nb	Ni	O	P	S	Se
1	0.005	0.0006	0.0538	0.040	0.120	0.0532	0.840	0.010	0.00158	0.0029	35.74	0.00193	0.0090	0.00113	0.19
2	0.0026	0.0012	0.054	0.0423	0.121	0.052	0.827	0.0125	0.0014	0.005	36.00	0.0016	0.0109	0.0007	0.208
3	0.0010	0.0012	0.0546	0.030	0.115	0.0534	0.806	0.01	0.00145	0.0021	36.03	0.00165	0.009	0.00067	0.16
4	0.001	0.00022	0.05333	0.0346	0.119	0.0515	0.8150	0.0095	0.0017	0.0017	35.769	0.0030	0.0091	0.00107	0.211
5	0.002	0.0010	0.054	0.0349	0.1206	0.052	0.831	0.0113	0.0020	0.002	35.833	0.0027	0.0093	0.0011	0.176
6	0.0024	0.0013	0.0521	0.039	0.120	0.052	0.805	0.008	0.0013	0.0043	35.884	0.00275	0.0088	0.0010	0.2400
7	0.0016	0.0003	0.054	0.035	0.118	0.0505	0.8151	0.010	0.0022	0.0088	36.00	0.0033	0.008	0.0012	0.161
8	0.0009	0.0011	0.0522	0.0375	0.1268	0.0496	0.8161	0.013	0.0021	0.002	35.839	0.0038	0.0094	0.000845	0.14457
9	0.003333		0.0545	0.0372	0.125	0.051	0.815	0.012	0.001736	0.0080	35.7876	0.00267	0.0106	0.00095	0.225
10	0.0049		0.0535	0.040	0.123	0.0515	0.832	0.0095	0.0010	0.0017	35.90	0.0035	0.0092	0.00090	0.166
11	0.0010		0.054996	0.0295	0.1194	0.0551	0.8384	0.0101	0.00174	0.0025	35.795	0.00106	0.008	0.0010	
12	0.0019		0.053	0.0316	0.118	0.053	0.835	0.011	0.0023	0.0067	35.814		0.011		
13			0.0534	0.034	0.122	0.0530	0.823	0.0110			35.79		0.0083		
14			0.0512	0.0324	0.1246	0.0513	0.8065	0.0104			35.837		0.0083		
15				0.0425							35.89		0.0100		
Mean	0.0023	0.0009	0.0535	0.0360	0.1209	0.0521	0.8218	0.0106	0.0017	0.0040	35.8606	0.0025	0.0093	0.0010	0.1882
STDV.	0.0014	0.0004	0.0011	0.0042	0.0032	0.0014	0.0122	0.0013	0.0004	0.0026	0.0895	0.0009	0.0010	0.0002	0.0317
Certified	0.002	(0.001)	0.053	0.036	0.121	0.052	0.82	0.011	0.0017	<0.01	35.86	0.003	0.009	0.0010	0.19
95% C.I.	0.001		0.001	0.002	0.002	0.001	0.01	0.001	0.0002		0.05	0.001	0.001	0.0001	0.02
Methods	X,I,O	I,O	C,O	X,I,O	X,I,O	X,I,O	X,I,O	X,I,O	F,O	X,I,O	X,W,I,O	F	X,I,O	X,C,O	X,A,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

24B	Si	Sn	Ta	Ti	V	W	Ag	As	Bi	Ca	Fe	Mg	Pb	Zn	Zr
1	0.290	0.0014	0.0038	0.0008	0.0022	0.01	0.002	0.0025	<0.005	0.0011	62.97	<0.001	0.0002	<0.005	0.0006
2	0.277	0.0025	0.0006	0.0008	0.0026	0.0355	0.00028	0.0038	0.0004	<0.0001	62.623	0.0004	0.0002	0.0015	0.0009
3	0.27	0.0014	0.001	0.001	0.0026	0.0045	0.00011	0.0025	0.00003	<0.001	62.72		0.00014	0.00075	0.0048
4	0.281	0.0017	0.00223	0.004	0.002	0.016		0.0031	0.000026	0.001	62.76		0.0015	0.0013	0.002
5	0.268	0.0020	0.0050	0.0015	0.0073	0.005			<0.001	0.0007	62.5902		0.0027		0.00082
6	0.277	0.00156	0.0007	0.0031	0.00412	0.0030			0.0000126	<0.0001	62.475		0.00015		0.0044
7	0.285	0.0010	0.0012	0.0033	0.0073	0.00892			0.000016		62.81				
8	0.2787	0.0020	0.0035	0.0019	0.0021	0.035			0.0373		62.56				
9	0.2805	0.0019		0.0010	0.0009	0.028					62.289				
10	0.281	0.0020		0.0030	0.0019	0.045									
11	0.270	0.0020			0.0032	0.0065									
12	0.287				0.0060	0.036									
13	0.286					0.0349									
14	0.2788														
Mean	0.2795	0.0018	0.0023	0.0020	0.0035	0.0206	0.0008	0.0030	0.0063	0.0009	62.6441	0.0004	0.0008	0.0012	0.0023
STDV.	0.0063	0.0004	0.0017	0.0012	0.0022	0.0153	0.0010	0.0006	0.0152	0.0002	0.1994		0.0011	0.0004	0.0019
Certified	0.28	0.0018	<0.005	0.002	<0.005	<0.04		<0.005			62.6				<0.005
95% C.I.	0.004	0.0003		0.001							0.2				
Methods	X,W,I,O	X,I,O	X,I,O	X,I,O	X,I,O	X,I,O		I			X,W,I,O				X,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981- (E) list the following:

Certifying Body: A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.


Reference Material (RM): A material or substance with one or more properties, which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

Methods of Analysis: In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. Each member of the ILAP is furnished a sample pack from a specific location on the batch bar. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.

Certified by: 
 William D. Britt, President/General Manager
 Analytical Reference Materials International

Certificate No.: 24B-08092007-ARM-F
 Certificate Date: 08/09/2007
 Revision Date/No.: 08/09/2007