

Analytical Reference Materials International

Certificate of Analysis Certified Reference Material



Grade: **MP159 / UNS R30159**

Part Number (Q.A. NO.): **IARM 256A**

Certification Date: **02/16/2001**

Certificate No.: **256A-02162001-IARM-F**

Revision Date: **05/05/2005**

Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a **parentheses ()** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets []** indicates **further testing is in process**.
4. The **"±Estimated Uncertainty"** is enclosed by a **parentheses ()** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Aluminum</u>	<u>Boron</u>	<u>Carbon</u>	<u>Cobalt</u>	<u>Chromium</u>	<u>Copper</u>	<u>Iron</u>	<u>Magnesium</u>
0.17 (0.01)	0.013 (0.002)	0.020 (0.002)	35.6 (0.4)	19.1 (0.1)	0.008 (0.002)	9.0 (0.2)	<0.001
<u>Manganese</u>	<u>Molybdenum</u>	<u>Nitrogen</u>	<u>Niobium</u>	<u>Nickel</u>	<u>Oxygen</u>	<u>Phosphorus</u>	<u>Sulfur</u>
0.014 (0.003)	7.0 (0.1)	0.0032 (0.0002)	0.51 (0.02)	25.7 (0.2)	0.0011 (0.0002)	0.006 (0.001)	0.002 (0.001)
<u>Silicon</u>	<u>Tantalum</u>	<u>Tin</u>	<u>Titanium</u>	<u>Tungsten</u>	<u>Vanadium</u>	<u>Zirconium</u>	
0.07 (0.01)	<0.005		3.03 (0.07)	0.02 (0.01)	0.03 (0.01)	(0.005)	

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Allvac - Monroe, NC
Anderson Laboratories, Inc. - Greendale, WI
Deloro Stellite - Belleville, ON
Howmet Dover Alloy - Dover, NJ
Laboratory Testing, Inc. - Hatfield, PA
Staveley Services Materials Testing - Gary, IN

Allvac Lockport - Lockport, NY
Cannon Muskegon Corp. - Muskegon, MI
Haynes International, Inc. - Kokomo, IN
Howmet Research Center - Whitehall, MI
Special Metals IncoTest - Hereford, England
Timken Latrobe Steel Co. - Latrobe, PA

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs and RMs applicable to the material covered by this certificate are: NIST 1775, MBH X403F, CT 175, BS 172A, ALV C05, LECO 501-674, 501-643, BS 193A, 172A, 170B, IARM 64B, LECO 501-550, NIST 1243, 1199, 1200, HAS 188A, 4005A, 200P, 750F, U 3933, 3934, LECO 501-503, 501-551, 502-102, BCS 351, 454/1, 462/1, NIST 131F, 72G, NIST 3107, 101G, 3131A, 3127A, BS CSN4, LECO 501-644, 501-643, 501-646, ECRM 295-1, NIST 16f, 123b, 132b, 134a, 135, 155, 160b, 168, 173b, 343a, 348a, 349a, 361, 363, 364, 367, 661, 1187, 1208-1, 1254, 1765, 2165, c2402, 2423, 2424a, 2425a, 3167, LECO 501-553, 502-01, NIST 1200, 167, IARM 64B, 207A, IARM 95A, 96A, 97A, 64A, WILLAN X401/A, X403/A, 14937N, 14936M, 12670F, BOHLER 8939, LECO 502-193, 502-194, NIST 3107, 2159, 349, 3131A, 3132, 3165, 3163, 3169, 3103A, 3106, 3127A, 3128, 3102A, 3149, 3155, 3167A, 3105A, ERN 328/1, IARM 64A, 126709, RC011, RC014, BS 3b, LECO 501-643, SPEX 8-49Al-X, 8-5B, 7-156Co, 7-107Cr, 7-140Cu, 7-179Fe, 7-62Mg, 7-116Mn, 8-7Mo, 7-96Nb, 7-139Ni, 7-120P, 8-27Si-A-X, 7-115Ti, 7-135V, 8-1W, 8-96Zr, 7-67Ag, 7-50As, 7-148Bi, 8-30La-Y, 7-67Pb, 7-102Sb, 7-50Se, 7-68Sn, 7-122Ta, 8-39Y-X, LECO 501-505, IARM 64A, 126709, RC011, RC014

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

700 Corporate Cr., Suite A • Golden, Colorado 80401 • Telephone (303) 216-2621 • FAX (303) 216-2649

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 05/05/2005.

256A	Al	B	C	Co	Cr	Cu	Fe	Mg	Mn	Mo	N	Nb	Ni	O	P
1	0.16	0.010	0.018	35.81	19.29	0.005	8.88	0.0035	0.010	7.11	0.0038	0.490	26.60	0.0009	0.007
2	0.1664	0.0147	0.0187	35.20	18.91	0.004	8.88	<0.001	0.01	7.10	0.0033	0.49	25.0	0.0013	0.0086
3	0.20	0.0058	0.019	34.8	19.4	0.008	9.3	0.00001	0.02	7.2	0.0033	0.55	25.75	0.0013	0.004
4	0.18	0.016	0.0184	35.0	18.91	0.0085	9.23	0.0006	0.01	7.04	0.0035	0.54	25.31	0.0010	0.007
5	0.18	0.014	0.0274	35.46	19.12	0.0038	9.24	<0.002	0.02	6.97	0.0030	0.52	25.72	0.0011	0.006
6	0.176	0.0141	0.0183	35.779	18.96	0.009	8.92	<0.001	0.012	6.98	0.0028	0.517	25.94	0.0012	0.0052
7	0.167	0.017	0.019	35.58	19.051	0.013	8.98	0.0008	0.019	7.094	0.0030	0.545	25.721		0.0045
8	0.17	0.0092	0.018	35.62	19.05	0.011	9.098	<0.002	0.023	7.05	0.0027	0.57	25.77		0.005
9	0.125	0.0166	0.019	36.786	19.02	0.0074	8.91		0.015	6.94	0.00289	0.450	25.88		0.005
10	0.1864	0.0176	0.026	36.581	19.111	0.0060	8.75		0.0121	6.794	0.0034	0.442	25.328		0.0085
11	0.1446	0.0168	0.0207	35.26	19.127		9.543		0.0128	6.917	0.0036	0.5076	25.472		0.0021
12	0.158	0.0099	0.018		19.26		8.568		0.008	7.14		0.49	26.20		0.0037
13	0.1534		0.0240				9.34			6.96		0.536	25.88		0.0064
14							8.30								
Mean	0.1667	0.0135	0.0203	35.6251	19.1008	0.0076	8.9956	0.0012	0.0143	7.0227	0.0032	0.5114	25.7362	0.0011	0.0056
STDV.	0.0193	0.0038	0.0033	0.6111	0.1526	0.0030	0.3285	0.0016	0.0050	0.1095	0.0004	0.0382	0.4089	0.0002	0.0019
Certified	0.17	0.013	0.020	35.6	19.1	0.008	9.0	<0.001	0.014	7.0	0.0032	0.51	25.7	0.0011	0.006
95% C.I.	0.01	0.002	0.002	0.4	0.1	0.002	0.2		0.003	0.1	0.0002	0.02	0.2	0.0002	0.001
Methods	X,I,O	I,O	C,O	X,W,I,O	X,W,I,O	X,G,I,O	X,W,I,O	G,D,A,I,O	X,G,I,O	X,I,O	F	X,I,O	X,W,I,O	F	X,G,W,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

256A	S	Si	Ta	Ti	V	W	Ag	As	Bi	Ca	La	Pb	Sb	Sn	Zr
1	0.002	0.080	0.00038	2.90	0.017	0.022	<0.0001	0.0008	<0.0001		<0.000001	<0.0001	0.0001	0.0011	0.006
2	0.0020	0.069	0.0021	2.86	0.025	0.05	0.000002	0.00046	<0.000001		<0.01	<0.000001	0.000048	0.00011	0.004
3	0.0019	0.08	0.0216	3.10	0.030	0.008	<0.01	<0.001	<0.001		0.0022	<0.0001	<0.01	0.01	0.0006
4	0.0017	0.092	0.0067	2.99	0.03	0.008	<0.0001	0.0002	0.0002		<0.002	0.0161	<0.0001	0.0023	0.003
5	0.0001	0.070	0.0056	2.99	0.018	0.02		<0.0001	<0.00003			<0.0001	<0.0001	0.0002	0.0032
6	0.0020	0.060		2.97	0.032	0.0024						<0.0001		0.0243	0.0103
7	0.0022	0.049		3.095	0.038	0.012						0.0109			
8	0.0018	0.061		3.02	0.012	0.033									
9	0.0031	0.0608		3.04	0.0541	0.010									
10	0.004	0.085		3.195	0.020	0.0424									
11	0.0028	0.0608		2.97	0.0432	0.0022									
12	0.0015			3.195		0.0026									
13	0.0002					0.0091									
14	0.0019														
Mean	0.0019	0.0698	0.0073	3.0271	0.0290	0.0171	0.0000	0.0005	0.0002		0.0022	0.0135	0.0001	0.0063	0.0045
STDV.	0.0010	0.0130	0.0084	0.1044	0.0125	0.0157		0.0003				0.0037	0.0000	0.0096	0.0033
Certified	0.002	0.07	<0.005	3.03	0.03	0.02									(0.005)
95% C.I.	0.001	0.01		0.07	0.01	0.01									
Methods	C,O	X,G,I,O	G,I,O	X,I,O	X,G,I,O	X,G,I,O									X,G,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981-(E) list the following:

Certifying Body: A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.


Reference Material (RM): A material or substance with one or more properties which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

Methods of Analysis: In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. Each member of the ILAP is furnished a sample pack from a specific location on the batch bar. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.

Certified by: 
 William D. Britt, President/General Manager
 Analytical Reference Materials International

Certificate No.: 256A-02162001-IARM-F
 Certification Date: 02/16/2001
 Revision Date/No.: 05/05/2005