

Analytical Reference Materials International

Certificate of Analysis Certified Reference Material



Grade: **Hastelloy® C-2000™ / UNS N06200**

Part Number (Q.A. NO.): **IARM 258A**

Certificate Date: **05/08/2006**

Certificate No.: **258A-05082006-IARM-F**

Revision Date: **05/08/2006**

Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a **parentheses ()** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets []** indicates **further testing is in process**.
4. The **"±Estimated Uncertainty"** is enclosed by a **parentheses ()** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Aluminum</u> 0.30 (0.02)	<u>Boron</u> 0.001 (0.0004)	<u>Carbon</u> 0.005 (0.001)	<u>Cobalt</u> 0.083 (0.004)	<u>Chromium</u> 22.8 (0.1)	<u>Copper</u> 1.54 (0.02)	<u>Iron</u> 0.85 (0.01)	<u>Lead</u> <0.0005
<u>Magnesium</u> 0.009 (0.002)	<u>Manganese</u> 0.21 (0.01)	<u>Molybdenum</u> 15.5 (0.1)	<u>Nitrogen</u> 0.032 (0.001)	<u>Niobium</u> 0.01 (0.005)	<u>Nickel</u> 58.6 (0.1)	<u>Oxygen</u> 0.0009 (0.0001)	<u>Phosphorus</u> 0.005 (0.001)
<u>Silicon</u> 0.015 (0.004)	<u>Sulfur</u> 0.0007 (0.0002)	<u>Tantalum</u> <0.01	<u>Tin</u> <0.001	<u>Titanium</u> 0.003 (0.001)	<u>Tungsten</u> 0.14 (0.01)	<u>Vanadium</u> 0.014 (0.001)	<u>Zirconium</u> <0.005

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Allvac - Monroe, NC

Anderson Laboratories, Inc. - Greendale, WI

Carpenter Technology Corporation - Reading, PA

Huntington Alloys Corporation - Huntington, WV

Rautaruukki Oyj - Raahel, Finland

Staveley Services Materials Testing - Gary, IN

Allvac Lockport - Lockport, NY

Cannon Muskegon Corp. - Muskegon, MI

Haynes International, Inc. - Kokomo, IN

Laboratory Testing, Inc. - Hatfield, PA

Special Metals IncoTest - Hereford, UK

Timken Latrobe Steel Co. - Latrobe, PA

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs and RMs applicable to the material covered by this certificate are: NIST 131g, 1243, Haynes 30229, 30701, 30702, 30703, 30704, 30705, 30706, CMC VV804, LECO 501-644, 501-643, NIST 898, 899, 3131A, 3161A, LECO 501-504, 501-674, 501-676, SS 387, A2236, IARM 54C, MBH 11124, JSS 651-3, AR 663, ECRM 196-1, LECO 501-645, 501-550, BCS 351, NIST 362, 3107, 101G, 362, 348, 166C, 126C, CECO 501-643 - 501-647, 501-501, 501-504, 501-502, 501-676, BS H2B, H6A, H7, CT 735, LECO 502-256, NIST 131G, 160B, HAS 25-6A, C276A, C276B, 400M, 400T, 600C, 600T, 718Q, 805B, 902B, LECO 502-256, 501-550, NIST 16F, 123B, 132B, 134A, 135, 155, 160B, 168, 173B, 343A, 345, 348A, 349A, 361, 363, 364, 367, 661, 1187, 1254, 1765, 2165, C2402, 2423, 2424A, 2425A, 3167, LECO 501-553, 502-016, Haynes 718, H-5, NIST 864, 867, 349, 131F, BCS 345, BS H7, IARM 56A, 63A, 65B, IMS 104, LECO 501-551, NIST 362, IARM 27C, 66A, 66B, IS0080A, 0081A, IC 93147, LECO 501-647, NIST 2159, 865, IARM 53B, ALPHA AR 511, LECO 501-503, 501-643, 501-645, BS 825, H3B, H2B, IARM 54C, 62B, LECO 502-102, 501-553, 502-148, NIST 1248, 2159, IARM 53B, 57B, 60A, 63B, 69B, 201A, BS H6, 200-1, MBH 11227C

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 05/08/2006.

258A	Al	B	C	Co	Cr	Cu	Fe	Mg	Mn	Mo	N	Nb	Ni	O	P
1	0.27	0.0010	0.005	0.073	22.69	1.580	0.877	0.005	0.230	15.74	0.0295	0.001	58.466	0.0008	0.003
2	0.320	0.0010	0.0063	0.091	22.876	1.47	0.826	0.008	0.198	15.566	0.0303	0.019	58.902	0.0009	0.0048
3	0.310	0.0008	0.0054	0.077	22.819	1.504	0.852	0.012	0.199	15.44	0.0321	0.012	58.70	0.0009	0.0053
4	0.280	0.0004	0.00569	0.091	23.08	1.580	0.860	0.0086	0.215	15.51	0.033	0.003	58.72	0.0009	0.0026
5	0.344	0.0003	0.0045	0.075	22.79	1.580	0.88	0.010	0.206	15.43	0.0330	0.015	58.70	0.0010	0.005
6	0.267	0.0001	0.0067	0.0853	22.76	1.57	0.857	0.0082	0.207	15.405	0.0318	0.0039	58.74	0.00076	0.0066
7	0.267	0.0005	0.00554	0.089	23.06	1.57	0.84	0.012	0.203	15.51	0.0353	0.017	58.58	0.0009	0.0047
8	0.267	0.0017	0.0054	0.092	22.69	1.53	0.83	0.0079	0.198	15.43	0.028	0.022	58.868	0.0011	0.0047
9	0.318		0.0042	0.080	22.77	1.56	0.82	0.006	0.186	15.57	0.0284	0.014	58.543		0.0012
10	0.324		0.0061	0.080	22.95	1.55	0.848	0.011	0.218	15.348	0.0319	0.0053	58.475		0.0073
11	0.319		0.0054	0.0768	22.575	1.513	0.8654	0.0087	0.200	15.764	0.0328	0.026			0.0065
12	0.2840		0.0091	0.0812	22.898	1.489	0.828	0.005	0.2172		0.0321	0.0184			0.0076
13	0.300		0.0037			1.525			0.2197		0.0318				
14			0.0085												
Mean	0.2977	0.0007	0.0058	0.0826	22.8298	1.5401	0.8486	0.0085	0.2075	15.5194	0.0315	0.0131	58.6698	0.0009	0.0049
STDV.	0.0265	0.0005	0.0015	0.0068	0.1511	0.0376	0.0201	0.0024	0.0119	0.1335	0.0020	0.0081	0.1514	0.0001	0.0019
Certified	0.30	0.001	0.005	0.083	22.8	1.54	0.85	0.009	0.21	15.5	0.032	0.01	58.6	0.0009	0.005
95% C.I.	0.02	0.0004	0.001	0.004	0.1	0.02	0.01	0.002	0.01	0.1	0.001	0.005	0.1	0.0001	0.001
Methods	X,A,I,O	D,I,O	C,O	X,I,O	X,W,I,O	X,I,O	X,I,O	X,A,I,O	X,I,O	X,W,I,O	F,O	X,I,O	X,W,I,O	F	X,W,A,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

258A	S	Si	Ta	Ti	V	W	Ag	As	Bi	Ca	La	Pb	Sb	Sn	Zr
1	0.0009	0.020	0.0055	0.006	0.018	0.10	0.00014	0.00043	<0.00005	0.0007	0.00004	0.0010	0.0007	0.0010	0.0036
2	0.0004	0.023	0.005	0.0019	0.015	0.117	0.0001	0.0006	<0.0001	0.005		0.00006	0.0005	0.0005	0.007
3	0.0003	0.013	0.0012	0.0043	0.013	0.144	0.00014	0.00094	0.001			0.00002	0.00095	0.00044	0.007
4	0.0004	0.013	0.0085	0.0022	0.015	0.137		<0.01	<0.0001			0.0010	0.0002	0.0002	0.0026
5	0.0007	0.01	0.0077	0.0056	0.012	0.116		0.0003				0.00004		0.00041	0.0005
6	0.00054	0.011		0.0038	0.0115	0.127						0.00003		0.0015	0.0019
7	0.0005	0.014		0.0006	0.011	0.147						0.0001			0.0004
8	0.0009	0.025		0.0021	0.015	0.143									0.0005
9	0.0003	0.014		0.0043	0.016	0.16									
10	0.0013	0.005			0.0159	0.160									
11	0.0006				0.0148	0.129									
12	0.0013					0.1303									
13						0.1600									
Mean	0.0007	0.0148	0.0056	0.0034	0.0143	0.1362	0.0001	0.0006	0.0010	0.0029	0.0000	0.0003	0.0006	0.0007	0.0029
STDV.	0.0004	0.0061	0.0029	0.0018	0.0022	0.0187	0.0000	0.0003		0.0030		0.0005	0.0003	0.0005	0.0028
Certified	0.0007	0.015	<0.01	0.003	0.014	0.14		<0.001				<0.0005	<0.001	<0.001	<0.005
95% C.I.	0.0002	0.004		0.001	0.001	0.01									
Methods	C,O	X,A,I,O	X,I,O	X,I,O	X,I,O			D,H,A,I				D,H,A,I	A,I,O	H,A,I	X,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981- (E) list the following:

Certifying Body: A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.


Reference Material (RM): A material or substance with one or more properties, which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

Methods of Analysis: In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. Each member of the ILAP is furnished a sample pack from a specific location on the batch bar. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.

Certified by: 
 William D. Britt, President/General Manager
 Analytical Reference Materials International

Certificate No.: 258A-05082006-ARM-F
 Certificate Date: 05/08/2006
 Revision Date/No.: 05/08/2006