

Analytical Reference Materials International

Certificate of Analysis Certified Reference Material



Grade: CDA 947 / UNS C94700

Part Number (Q.A. NO.): IARM 267A

Certificate Date: 11/26/2008

Certificate No.: 267A-11262008-IARM-F

Revision Date: 11/26/2008

Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a **parentheses ()** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets []** indicates **further testing is in process**.
4. The "**±Estimated Uncertainty**" is enclosed by a **parentheses ()** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Aluminum</u> 0.003 (0.001)	<u>Antimony</u> <0.03	<u>Arsenic</u> (0.004)	<u>Bismuth</u> (0.005)	<u>Carbon</u> (0.003)	<u>Chromium</u> (0.001)	<u>Cobalt</u> 0.002 (0.001)
<u>Copper</u> 87.8 (0.1)	<u>Iron</u> 0.019 (0.001)	<u>Lead</u> 0.026 (0.003)	<u>Manganese</u> 0.002 (0.001)	<u>Nickel</u> 5.1 (0.1)	<u>Nitrogen</u>	<u>Oxygen</u>
<u>Phosphorus</u> 0.037 (0.002)	<u>Selenium</u> 0.002 (0.001)	<u>Silicon</u> 0.003 (0.001)	<u>Silver</u> 0.002 (0.002)	<u>Sulfur</u> 0.0014 (0.0003)	<u>Tin</u> 4.95 (0.04)	<u>Zinc</u> 2.06 (0.04)

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Anderson Laboratories, Inc. - Greendale, WI

AY Mc Donald Mfg. Co. - Dubuque, IA

Bodycote Testing - Portland, OR

Colonial Metals Co. - Columbia, PA

I. Schumann & Company - Bedford, OH

Riverside Brass & Aluminum Foundry Ltd. - New Hamburg, ON

Stork Materials Testing and Inspection - Huntington Beach, CA

Atlas Pacific Corporation - Colton, CA

Berntsen Brass & Aluminum Foundry, Inc. - Madison, WI

California Metal-X - Los Angeles, CA

Concast Metal Products Co. - Mars, PA

Laboratory Testing, Inc. - Hatfield, PA

Sipi-Metals Corp - Chicago, IL

The Federal Metal Co. - Bedford, OH

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs, and RMs applicable to the material covered by this certificate are: IARM 70A, 71A, 72A, 73A, 74A, 75A, 76A, 77A, 78A, 79A, 80B, 81A, 82A, 83A, 84B, 85B, 86B, 87A, 88A, 89B, 90B, 91B, 92B, 93B, 94A, 32X SEB1A, SEB2A, SEB4A, SEB5A, 31X WSB1B, WSB2A, WSB4A, WSB5A, 33X GM5D, BS 954A, CC865, 876, BAM-376, BAS 50.01-4, 54.03-4, BNF C11.02-1, C11.03-0, C30.08-1, C50.03-3, C71.32-3, BS 903, 903B, 110A, 314B, 706A, 836, 922A, 932, 932A, 932M-OLD, 932M-NEW, 938-1, CC905, CKD 318, 319, 320, 321, 322, 323, CONCAST 2172385, 2173895, 2189586, 54850, CTIF 4583, 4873, B22, B30, B31, B32, UE14, UE15.1, UE40, UE53-1, MBH 14953-C, 14954-B, 14956-B, 14958-B, 17866-K, 17868-S, 17869-Y, 17869-R, 17870-K, 17870-S, 31X/B8-F, 32X/LB14-A, 32X/LB8-A, 32X/PB5-H, 32X/SEB5-A, 32X/SEB6-A, 32X/LB1/G, 32X/LB2/F, 32X/LB15-A, 32X/SN3, 32X/GM4-D, 32X/GM5-D, 32X/GM6-D, 32X/GM7-D, TEKM PB8C, PB9A, WILLAN PB1L, PB2J, PB4H, BCS 183/4, LECO 501-503, 501-643, AR 512, 147, IARM 78B, 90B, 226A, 227A, 228A, CKD 318, 319, 33XGM4, B21, IARM 227A, 32X SEB3A, SEB5A, SEB6A, CA 927, NIST C1253, IARM 90B, 86B, MBH 178700, LECO 501-550, 501-673, NIST 1102, IARM 86B, 92B, 32X SEB3, SEB6, LECO 501-501, 501-550, IARM 90B, 91B, 92B, 250A, NIST C1103, IARM 70A, 70B, 71A, 72A, 73A, 74A, 75A, 76A, 77A, 78A, 79A, 80A, 81A, 83A, 84A, 85A, 85B, 86B, 87A, 89A, 91A, 91B, 92A, 93A, 93B, 94A, 94B, 150A, 151A, 204A, BS 172BE, 360A, 464A, 482A, 510A, 655A, 706A, 706B, 715A, 863A, 903B, 954A, LECO 501-675, IARM 226A, 227A, 228A, 250A, BS 544A, 836, 836A-1, 922A, 932A, 932M, 937, 31XB21, 31XB22, 31XCB23.1, 32XB5, 32XSEB1, 32XSEB2, 32XSEB3, 32XSEB4, 32XSEB5, 32XSEB6, 33XGM4, CTIF UZ50, UZ51, UZ53, C50.03, C54.05, C54.06, 7132, 7133, M871, M872, M873, M874, M875, 32XSEB1, 32XSEB2, 32XSEB3, 32XSEB4, 32XSEB5, 32XSEB6, NIST 184, IARM 227A, 228A, BS 932E, 33XGM4-W, IARM 73A, 80A, 89A, 226A, 227A, 228A, NIST 1104, 1107, 1111, 1112, 1113, BS 715, IARM 86A.

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

700 Corporate Cr., Suite A • Golden, Colorado 80401 • Telephone (303) 216-2621 • FAX (303) 216-2649

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 11/26/2008.

267A	Ag	Al	As	Be	Bi	C	Co	Cr	Cu	Fe	Mn	Nb	Ni	P	Pb
1	0.0018	0.0025	0.0051	0.0002	0.008	0.0043	0.0032	0.0018	87.5171	0.0200	0.0032	0.0002	5.09	0.035	0.0280
2	0.0008	0.0049	0.0010	0.0001	0.001	0.005	0.0022	0.0007	87.88	0.019	0.003	0.039	5.061	0.0395	0.025
3	0.00183	0.0032	0.0011	<0.0005	0.0026	0.0008	0.0035	0.00215	87.716	0.0221	0.0027	<0.01	5.168	0.0438	0.0188
4	0.003	0.0015	0.0057	<0.005	0.0073	0.003	0.0022	0.001	87.807	0.0155	0.0003	<0.005	4.922	0.040	0.0280
5	0.0015	0.0004	0.006		0.00415		0.0026	0.001	87.677	0.0209	0.00208	0.025	5.073	0.031	0.0275
6	0.0030	0.0035	0.001		0.007		0.0020		87.848	0.0172	0.0027		5.10	0.040	0.01766
7		0.004	0.0085		0.0057		0.002		88.1	0.017	0.0038		5.28	0.037	0.025
8		0.0020	0.0010		0.001		0.0015		87.89	0.018	0.0012		5.003	0.0404	0.0317
9		0.0015	0.0039		0.01				87.4267	0.0236	0.003		5.2504	0.0398	0.029
10		0.0033							88.18	0.0166	0.0025		5.1867	0.035	0.024
11		0.003							87.818	0.020	0.0004			0.039	0.0267
12		0.001								0.016				0.030	
13		0.0050								0.02				0.0317	
14		0.0029								0.0181				0.037	
Mean	0.0020	0.0028	0.0037	0.0002	0.0052	0.0033	0.0024	0.0013	87.8054	0.0189	0.0023	0.0214	5.1134	0.0371	0.0256
STDV.	0.0009	0.0014	0.0028	0.0001	0.0032	0.0018	0.0007	0.0006	0.2220	0.0024	0.0012	0.0196	0.1100	0.0041	0.0042
Certified	0.002	0.003	(0.004)		(0.005)	(0.003)	0.002	(0.001)	87.8	0.019	0.002		5.1	0.037	0.026
95% C.I.	0.001	0.001				0.001			0.1	0.001	0.001		0.1	0.002	0.003
Methods	I,O	I,O	X,I,O		X,A,I,O	C,O	X,I,O	X,I,O	X,W,I,O	X,I,O	X,I,O		X,A,I,O	X,I,O	X,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = AES, X = XRF, G = GDAES or GDMS, H = Hollow Cathode AES

267A	S	Sb	Se	Si	Sn	Zn	Ce	La	Mg	Mo	Nd	N	O	Sm	Zr
1	0.0020	0.0050	0.0010	0.0012	5.0300	2.13	0.0022	0.0033	<0.0001	<0.0001	<0.0001	<0.0001	0.0027	<0.0001	0.0001
2	0.001	0.0265	0.0007	0.004	4.93	2.143	0.014	0.002	0.018	0.005	0.005	0.0007	0.0062	0.004	0.002
3	0.0011	0.0021	0.0015	0.0046	4.951	1.980	<0.01	<0.01	<0.001	<0.005	<0.01	<0.005	0.0017	<0.01	<0.01
4	0.0012	0.0287	0.005	0.0015	4.951	1.968		<0.005	<0.005						<0.005
5	0.0011	0.00817	0.0038	0.0021	5.103	1.958			<0.0001						
6	0.0012	0.0028	0.001	0.0026	4.8708	2.13									
7	0.001	0.0033	0.002	0.0032	5.07	2.10									
8	0.0021	0.0177	0.0006	0.0030	4.90	2.06									
9	0.001	0.0136		0.0014	4.87	2.073									
10	0.0021	0.006		0.0028	4.9592	2.009									
11	0.0012	0.0050		0.0045	4.925	2.056									
12		0.03		0.002	4.881	2.06									
13					4.99	2.171									
14					4.87										
Mean	0.0014	0.0124	0.0020	0.0027	4.9501	2.0645	0.0081	0.0027	0.0180	0.0050	0.0050	0.0007	0.0035	0.0040	0.0011
STDV.	0.0005	0.0107	0.0016	0.0012	0.0751	0.0698	0.0083	0.0009					0.0024		0.0013
Certified	0.0014	<0.03	0.002	0.003	4.95	2.06									
95% C.I.	0.0003		0.001	0.001	0.04	0.04									
Methods	C,O	X,I,O	I,O	I,O	X,W,I,O	X,I,O									

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = AES, X = XRF, G = GDAES or GDMS, H = Hollow Cathode AES

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1992 list the following:

Certifying Body: Any technically competent body (organization or firm, public or private) that issues a reference material certificate which provides the information detailed in ISO Guide 31. The only generally accepted certifying body in the United States for primary standards - Standard Reference Materials (SRM) is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD. All other certifying bodies in the United States produce Reference Materials (RM) or Certified Reference Materials (CRM).


Reference Material (RM): Material or substance one or more of whose property values are sufficiently homogeneous and well established to be used for the calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): Reference material, accompanied by a certificate, one or more of whose property values are certified by a procedure which establishes its traceability to an accurate realization of the unit in which the property values are expressed, and for which each certified value is accompanied by an uncertainty at a stated level of confidence.

Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

Methods of Analysis: In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. Each member of the ILAP is furnished a sample pack from a specific location on the batch bar. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.

Certified by: 
 William D. Britt, President/General Manager
 Analytical Reference Materials International

Certificate No.: 267A-11262008-IARM-F
 Certificate Date: 11/26/2008
 Revision Date/No.: 11/26/2008