

Analytical Reference Materials International

Certificate of Analysis Certified Reference Material



Grade: **A286 / UNS S66286**

Part Number (Q.A. NO.): **IARM 26C**

Certificate Date: **03/23/2009**

Certificate No.: **26C-03232009-IARM-F**

Revision Date: **04/20/2010**

Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a **parentheses ()** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets []** indicates **further testing is in process**.
4. The "**±Estimated Uncertainty**" is enclosed by a **parentheses ()** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Aluminum</u> 0.12 (0.004)	<u>Arsenic</u> 0.004 (0.001)	<u>Boron</u> 0.0074 (0.0003)	<u>Carbon</u> 0.028 (0.001)	<u>Calcium</u> (0.0002)	<u>Chromium</u> 13.7 (0.05)	<u>Cobalt</u> 0.052 (0.001)	<u>Copper</u> 0.144 (0.002)
<u>Magnesium</u> (0.0003)	<u>Manganese</u> 0.25 (0.003)	<u>Molybdenum</u> 1.09 (0.01)	<u>Nitrogen</u> 0.0045 (0.0003)	<u>Niobium</u> 0.002 (0.001)	<u>Nickel</u> 25.05 (0.03)	<u>Oxygen</u> 0.002 (0.0004)	<u>Phosphorus</u> 0.017 (0.001)
<u>Sulfur</u> 0.0004 (0.0001)	<u>Silicon</u> 0.08 (0.01)	<u>Tantalum</u> 0.002 (0.001)	<u>Tin</u> 0.011 (0.001)	<u>Titanium</u> 1.87 (0.01)	<u>Vanadium</u> 0.238 (0.002)	<u>Tungsten</u> 0.01 (0.002)	<u>Zirconium</u> (0.001)

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Alcoa Howmet, Dover Alloy - Dover, NJ
ATI Allvac, Monroe - Monroe, NC
Exova - Glendale Heights, IL
Exova - Portland, OR
Laboratory Testing, Inc. - Hatfield, PA
NSL Analytical Services - Cleveland, OH

ATI Allvac, Lockport - Lockport, NY
Carpenter Technology Corporation - Reading, PA
Exova - Los Angeles, CA
Huntington Alloys Corporation - Huntington, WV
Latrobe Specialty Steel Co. - Latrobe, PA
Special Metals IncoTest - Hereford, UK

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs, and RMs applicable to the material covered by this certificate are: NIST 348, 1194, NIST 1194, 1230, IARM 26B, BS 188A, CSN-4, LECO 501-643, ALPHA AR871, BS 188, LECO 501-506, 762-747, ALPHA AR660, AR869, NIST 121D, 348A, 3103A, 3106, 3109A, 3128, 3131A, 3137, 3149, 3155, 3161A, 3168A, 3169, ALPHA AR511, AR669, LECO 501-503, NIST 123C, IARM 26B, BS 188A, LECO 502-257, NIST 1230, IARM 25A, 26A, 26B, BS 188, LECO 501-506, 501-550, 501-675, 502-257, NIST 362, IARM 26B, 27D, IS0058A, IS0086A, HAS 286A, 400M, ALPHA AR881, LECO 501-644, NIST 131G, 272G, 1194, 1230, BCS 346A, BCS 342, 351, 454/1, 462/1, 464, HAS 250A, LECO 501-551, 502-102, R5657, NIST 867, 3102A, 3106, 3107, 3109A, 3131A, 3151, 3161A, BS 188A, LECO 501-147, 501-643, 501-991, BS 2363, 188A, NIST 1230, IARM 26B, CLAXTON C21.

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 04/20/2010.

26C	Al	B	C	Co	Cr	Cu	Mn	Mo	N	Nb	Ni	O	P	S	Se
1	0.1211	0.0080	0.027	0.050	13.80	0.140	0.258	1.08	0.0050	0.0009	25.10	0.00167	0.016	0.00056	<0.001
2	0.125	0.0074	0.029	0.0529	13.81	0.140	0.2595	1.110	0.00421	0.0006	25.069	0.00298	0.016	0.0004	0.0011
3	0.114	0.0075	0.0270	0.0569	13.766	0.1483	0.25	1.093	0.0044	0.0012	24.97	0.0029	0.0170	0.0006	<0.00001
4	0.1247	0.0073	0.0294	0.0519	13.75	0.1455	0.25195	1.10	0.0037	0.0029	25.046	0.0016	0.0169	0.00057	<0.00001
5	0.125	0.0074	0.0291	0.0511	13.610	0.1430	0.2546	1.09745	0.0037	0.00096	25.037	0.0025	0.0146	0.00015	0.0001
6	0.126	0.0072	0.029	0.0540	13.733	0.143	0.254	1.10	0.0049	0.0024	25.090	0.0016	0.0165	0.0002	<0.00003
7	0.124	0.0079	0.0274	0.0561	13.774	0.147	0.253	1.096	0.0045	0.003	25.146	0.0023	0.0181	0.0002	<0.0025
8	0.122	0.0080	0.0262	0.0527	13.889	0.142	0.253	1.091	0.0045	0.0038	25.02	0.0017	0.0182	0.00033	
9	0.112	0.0070	0.0274	0.050	13.79	0.141	0.251	1.09	0.0048		25.02	0.00191	0.0167	0.00023	
10	0.116	0.0066	0.0285	0.0485	13.60	0.145	0.260	1.120	0.0050		25.00	0.00142	0.0184	0.0005	
11	0.1073		0.0268	0.052	13.65	0.145	0.247	1.08	0.00468		25.050	0.0031	0.016		
12			0.0280	0.0495	13.680	0.1467	0.2451	1.081	0.00475		25.058		0.0173		
13			0.0254	0.0530	13.7393	0.1457	0.2410	1.0697					0.0157		
14					13.741			1.0724					0.0171		
Mean	0.1197	0.0074	0.0277	0.0522	13.7380	0.1440	0.2522	1.0915	0.0045	0.0020	25.0505	0.0022	0.0168	0.0004	0.0006
STDV.	0.0064	0.0004	0.0012	0.0025	0.0801	0.0027	0.0055	0.0141	0.0004	0.0012	0.0473	0.0006	0.0011	0.0002	0.0007
Certified	0.12	0.0074	0.028	0.052	13.7	0.144	0.25	1.09	0.0045	0.002	25.05	0.002	0.017	0.0004	
95% C.I.	0.004	0.0003	0.001	0.001	0.05	0.002	0.003	0.01	0.0003	0.001	0.03	0.0004	0.001	0.0001	
Methods	X,I,O	I,O	C,O	X,I,O	X,W,I,O	X,I,O	X,I,O	X,I,O	F	X,G,I,O	X,W,I,O	F,O	X,I,O	C,G,O	

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

26C	Si	Sn	Ta	Ti	V	W	Ag	As	Bi	Ca	H	Mg	Pb	Zn	Zr
1	0.083	0.009	0.0036	1.91	0.242	0.0143	<0.0005	0.0038	<0.00002	0.0004	0.0002	0.0005	<0.005	0.0014	0.0003
2	0.082	0.01035	0.0012	1.85	0.2406	0.0084	0.0002	0.0050	0.0053	0.0002		0.00030	<0.0001	0.0020	0.0007
3	0.0741	0.0124	0.0012	1.843	0.244	0.0103	0.00007	0.0023	<0.00001	0.00003		0.0002	0.0041	0.0024	0.0004
4	0.0742	0.0107	0.0009	1.87	0.2330	0.009	0.00007	0.0032	<0.00001	0.00023		0.00022	<0.00001	0.0022	0.0009
5	0.070	0.01003	0.001	1.887	0.242	0.0025	0.000045	0.0037	0.00001	0.0003			0.000011		0.00060
6	0.067	0.0100	0.004	1.87	0.242	0.0086		0.0030	<0.00001				0.00003		0.001
7	0.091	0.012	0.0020	1.858	0.231	0.010			<0.00003				0.000006		
8	0.093	0.0141		1.897	0.235	0.004							<0.00003		
9	0.080	0.0111		1.84	0.238	0.013							0.0024		
10	0.088	0.0119		1.900	0.236	0.0102									
11	0.077	0.0116		1.88	0.237	0.0103									
12	0.0841	0.0093		1.838	0.2417										
13				1.85237	0.2347										
14				1.856											
Mean	0.0803	0.0110	0.0020	1.8680	0.2382	0.0091	0.0001	0.0035	0.0027	0.0002	0.0002	0.0003		0.0020	0.0007
STDV.	0.0081	0.0014	0.0013	0.0236	0.0041	0.0034	0.0001	0.0009	0.0037	0.0001		0.0001		0.0004	0.0003
Certified	0.08	0.011	0.002	1.87	0.238	0.01		0.004		(0.0002)		(0.0003)		(0.002)	(0.001)
95% C.I.	0.01	0.001	0.001	0.01	0.002	0.002		0.001							
Methods	X,W,I,O	X,G,I,O	X,G,I	X,I,O	X,I,O	X,G,I,O		H,G,I,O		G,I,O		G,I		G,I	X,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1992 list the following:

Certifying Body: Any technically competent body (organization or firm, public or private) that issues a reference material certificate, which provides the information, detailed in ISO Guide 31. The only generally accepted certifying body in the United States for primary standards - Standard Reference Materials (SRM) is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD. All other certifying bodies in the United States produce Reference Materials (RM) or Certified Reference Materials (CRM).

Reference Material (RM): Material or substance one or more of whose property values are sufficiently homogeneous and well established to be used for the calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): Reference material, accompanied by a certificate, one or more of whose property values are certified by a procedure, which establishes its traceability to an accurate realization of the unit in which the property values are expressed, and for which each certified value is accompanied by an uncertainty at a stated level of confidence.


Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

Methods of Analysis: In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion and OE instrument procedures.

Expiration of Certification: The certification of this IARM is valid indefinitely, within the uncertainty specified, provided the IARM is handled and stored in accordance with the instructions stated on this certificate. The certification is nullified if the IARM is damaged, contaminated, otherwise modified, or used in a manner for which it was not intended.

Instructions for Use: The test surface is the side opposite to the labeled surface, which includes the IARM number. The entire thickness of the unit is certified. However, the user is cautioned not to measure disks less than 2 mm thick when using X-ray fluorescence spectrometry. Each packaged disk has been prepared by finishing the test surface using a lathe. The user must determine the correct surface preparation procedure for each analytical technique. The user is cautioned to use care when either resurfacing the disk or performing additional polishing as these processes may contaminate the surface. When not in use, the material should be stored in a cool, dry location. This material was tested using both the solid disks and chips prepared from the disks. The certified values are considered representative of the overall average composition of the material. **Chips are not to be used for Oxygen analysis.**

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.


 William D. Britt, President, & General Manager
 Analytical Reference Materials International Corporation

Certificate No.: 26C-03232009-IARM-F
 Certificate Date: 03/23/2009
 Revision Date/No.: 04/20/2010