

Certificate of Analysis IARM 27E

CP Iron / UNS K00095
Certified Reference Material

Certified Values listed in wt.% with associated uncertainties

ΑI	0.0008 ± 0.0003	As	0.0005 ± 0.0003	В	0.00040 ± 0.00008	C	0.0021 ± 0.0004
Co	0.0024 ± 0.0006	Cr	0.0012 ± 0.0006	Cu	0.0008 ± 0.0004	Mn	0.0012 ± 0.0004
Мо	0.0008 ± 0.0003	N	0.0003 ± 0.0002	Nb	0.0009 ± 0.0004	Ni	0.0046 ± 0.0006
0	0.007 ± 0.001	Р	0.0013 ± 0.0005	Pb	0.0006 ± 0.0004	S	0.0008 ± 0.0001
Sb	0.001 ± 0.001	Si	0.0030 ± 0.0004	Sn	0.0004 ± 0.0002	Ti	0.0005 ± 0.0002
٧	0.0004 ± 0.0002	W	0.002 ± 0.002	Zr	0.0004 ± 0.0003		

Indicative Values listed in ppm

Bi (<20) Ca (10) Mg (3)	Se (<80)	Ta (<19)	Zn (10)
-------------------------	----------	----------	---------

Description and Intended Use

This CRM may come in the form of a solid disc or chips. The intended use of this CRM may include, but is not limited to, the calibration of instruments and the validation of analytical methods.

Interpretation of Data

- 1. Certified values listed reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community, and are reported as wt% unless otherwise noted.
- 2. This material was tested using both the solid disks and chips prepared from individual sections of bar. The certified values are considered representative of the overall average composition of the material.
- 3. Any data reported and enclosed by a parentheses () is a "best estimate" and is not certified. This data could not be quantified sufficiently for certification. It was, however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
- 4. "Provisional Certificate of Analysis" reports values that support a fully certified reference material; it also indicates that values may be in a continued process of statistical evaluation and are subject to change.
- 5. Chips are not certified for Oxygen analysis.



1/3

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material.

				Б.	_		Δ-	•	0		14			NII.		
	Al	As	В	Bi	С	Ca	Со	Cr	Cu	Mg	Mn	Mo	N	Nb	Ni	0
1	0.0002	0.00007	0.00015	0.0002	0.0008	0.0001	0.0003	0.0003	0.0002	0.0001	0.00013	0.0001	0.00009	0.0001	0.002	0.006
2	0.0002	0.0001	0.0002	0.0021	0.001	0.0006	0.0009	0.0003	0.00045	0.0002	0.001	0.0002	0.0001	0.0004	0.003	0.0065
3	0.0003	0.0002	0.0003	0.0047	0.0016	0.0011	0.0019	0.0004	0.0005	0.0003	0.001	0.0002	0.0001	0.001	0.004	0.0066
4	0.0003	0.0005	0.0003	<0.00001	0.0017	0.002	0.0025	0.0006	0.0008	0.0003	0.001	0.0008	0.0001	0.001	0.0042	0.0068
5	0.0004	0.0005	0.0004	<0.0001	0.00177	<0.0001	0.0026	0.0008	0.0009	0.0004	0.001	0.0009	0.0001	0.001	0.0044	0.0068
6	0.00073	0.0006	0.0004	<0.0001	0.002	<0.0001	0.0026	0.001	0.001	<0.0001	0.0013	0.001	0.0002	0.001	0.0048	0.007
7	0.00077	0.0008	0.0004		0.0021	<0.0001	0.0027	0.0015	0.001	<0.0001	0.0013	0.001	0.0002	0.0012	0.0049	0.0072
8	0.0009	0.001	0.0005		0.0023	<0.0002	0.0029	0.0015	0.0017	<0.0003	0.0018	0.001	0.0002	0.0014	0.0049	0.0074
9	0.001		0.0005		0.00235	<0.0003	0.003	0.0016			0.0019	0.001	0.0003		0.0049	0.0089
10	0.001		0.0005		0.00244	<0.0005	0.003	0.002				0.0016	0.0005		0.005	0.0107
11	0.0011		0.0005		0.0025		0.003	0.003					0.0011		0.0052	
12	0.0017		0.0005		0.0027		0.0035								0.0053	
13	0.002		0.00053		0.0031										0.00531	
14					0.0031										0.006	
.15											0.0010				0.0040	
Mean	0.0008	0.0005	0.0004	0.002	0.0021	0.001	0.0024	0.0012	0.0008	0.0003	0.0012	0.0008	0.0003	0.0009	0.0046	0.007
STDV.	0.0006	0.0003	0.0001	0.002	0.0007	0.0008	0.0009	0.0008	0.0005	0.0001	0.0005	0.0005	0.0003	0.0004	0.001	0.001
Certified	0.0008	0.0005	0.00040	(0.002)	0.0021	(0.001)	0.0024	0.0012	0.0008	(0.0003)	0.0012	0.0008	0.0003	0.0009	0.0046	0.007
95% C.I.	0.0003	0.0003	0.00008		0.0004		0.0006	0.0006	0.0004		0.0004	0.0003	0.0002	0.0004	0.0006	0.001
Methods	G,I,IM,O	H,I,IM,O,X	G,I,IM,O	O,MI,I,H	C,O	1,0	G,I,IM,O,X	G.I.IM.O.X	I G.I.IM.O.X	O,MI,I,H	G,I,IM,O,X	G,I,IM,O,X	F,O	I G.I.IM.O.X	G,I,IM,O,X	F
				,,,,-	-,-			-11 1-1	-,,,,-,-,	,,,,	-,,,,-,	-,, ,-,		-,,,,,,,,	-,, ,-,	
	Р	Ph	S		•	•	Sn									
1	P	Pb	S	Sb	Se	Si	Sn	Та	Ti	V	W	Zn	Zr	I	- , , , - ,	
1 2	0.0007	0.00004	0.0005	Sb 0.0002	Se 0.008	Si 0.002	0.0001	Ta 0.0015	Ti 0.00006	V 0.0001	W 0.0002	Zn 0.00002	Zr 0.0001		.,,	
2	0.0007 0.00073	0.00004 0.00019	0.0005 0.00057	Sb 0.0002 0.0005	Se 0.008 <0.0001	Si 0.002 0.002	0.0001 0.0002	Ta 0.0015 0.002	Ti 0.00006 0.0002	V 0.0001 0.0001	W 0.0002 0.001	Zn 0.00002 0.0001	Zr 0.0001 0.0002			
	0.0007 0.00073 0.0009	0.00004 0.00019 0.0006	0.0005 0.00057 0.0006	Sb 0.0002 0.0005 0.0007	Se 0.008	Si 0.002 0.002 0.0024	0.0001 0.0002 0.0003	Ta 0.0015 0.002 0.0022	Ti 0.00006 0.0002 0.0002	V 0.0001 0.0001 0.0003	W 0.0002 0.001 0.001	Zn 0.00002 0.0001 0.0021	Zr 0.0001 0.0002 0.0002			
2	0.0007 0.00073 0.0009 0.001	0.00004 0.00019 0.0006 0.0008	0.0005 0.00057 0.0006 0.0006	Sb 0.0002 0.0005 0.0007 0.0008	Se 0.008 <0.0001	Si 0.002 0.002 0.0024 0.0025	0.0001 0.0002 0.0003 0.0003	Ta 0.0015 0.002 0.0022 <0.0001	Ti 0.00006 0.0002 0.0002 0.0003	V 0.0001 0.0001 0.0003 0.00038	W 0.0002 0.001 0.001 0.0011	Zn 0.00002 0.0001 0.0021 0.0021	Zr 0.0001 0.0002 0.0002 0.0004			
2 3 4	0.0007 0.00073 0.0009 0.001 0.001	0.00004 0.00019 0.0006 0.0008 0.00085	0.0005 0.00057 0.0006 0.0006 0.0007	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	Si 0.002 0.002 0.0024 0.0025 0.0028	0.0001 0.0002 0.0003 0.0003 0.0005	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004	V 0.0001 0.0001 0.0003 0.00038 0.0004	W 0.0002 0.001 0.001 0.0011 0.0012	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042			
2 3 4 5	0.0007 0.00073 0.0009 0.001 0.001 0.001	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008	Sb 0.0002 0.0005 0.0007 0.0008	Se 0.008 <0.0001	Si 0.002 0.002 0.0024 0.0025 0.0028 0.0028	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001 <0.001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004	V 0.0001 0.0001 0.0003 0.00038 0.0004 0.0004	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025	Zn 0.00002 0.0001 0.0021 0.0021	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006			
2 3 4 5	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001	0.00004 0.00019 0.0006 0.0008 0.00085	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.00085	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.0028 0.003	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005	V 0.0001 0.0001 0.0003 0.00038 0.0004 0.0004	W 0.0002 0.001 0.001 0.0011 0.0012	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042			
2 3 4 5 6 7	0.0007 0.00073 0.0009 0.001 0.001 0.001	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	Si 0.002 0.002 0.0024 0.0025 0.0028 0.0028	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001 <0.001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004	V 0.0001 0.0001 0.0003 0.00038 0.0004 0.0004	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006			
2 3 4 5 6 7 8	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.001 0.001	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.00085 0.0009	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.0028 0.003 0.0032 0.0033	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001 <0.001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007	V 0.0001 0.0003 0.0003 0.0003 0.0004 0.0004 0.0005 0.0008	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006			
2 3 4 5 6 7 8 9	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.001	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.00085 0.0009	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	Si 0.002 0.002 0.0024 0.0025 0.0028 0.0028 0.003 0.0032	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001 <0.001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007	V 0.0001 0.0003 0.0003 0.0003 0.0004 0.0004 0.0005 0.0008	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006			
2 3 4 5 6 7 8 9	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.001 0.0011	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.00085 0.0009 0.0009	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.0032 0.0033 0.0032	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001 <0.001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007 0.0007	V 0.0001 0.0003 0.0003 0.0003 0.0004 0.0004 0.0005 0.0008	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006			
2 3 4 5 6 7 8 9 10	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.0011 0.0011 0.0011	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.0008 0.0008 0.0009 0.0009 0.0009	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.003 0.0032 0.0033 0.0034 0.0036	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001 <0.001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007 0.0007	V 0.0001 0.0003 0.0003 0.0003 0.0004 0.0004 0.0005 0.0008	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006			
2 3 4 5 6 7 8 9 10 11 12 13	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.0011 0.0011 0.0011 0.0012 0.0017	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.0008 0.0008 0.0009 0.0009 0.0009	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.0028 0.0033 0.0032 0.0033 0.0034 0.0036 0.00371	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001 <0.001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007 0.0007	V 0.0001 0.0003 0.0003 0.0003 0.0004 0.0004 0.0005 0.0008	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006			
2 3 4 5 6 7 8 9 10 11 12 13	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.0011 0.0011 0.0011 0.0011	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.0008 0.0008 0.0009 0.0009 0.0009	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.0028 0.0033 0.0032 0.0033 0.0034 0.0036 0.00371	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001 <0.001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007 0.0007	V 0.0001 0.0003 0.0003 0.0003 0.0004 0.0004 0.0005 0.0008	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006			
2 3 4 5 6 7 8 9 10 11 12 13	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.0011 0.0011 0.0011 0.0012 0.0017	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.0008 0.0008 0.0009 0.0009 0.0009	Sb 0.0002 0.0005 0.0007 0.0008 0.0009 0.0035	Se 0.008 <0.0001 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.0028 0.0033 0.0032 0.0033 0.0034 0.0036 0.00371	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006 0.0008	Ta 0.0015 0.002 0.0022 <0.0001 <0.0001 <0.001	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007 0.0007	V 0.0001 0.0003 0.0003 0.0003 0.0004 0.0004 0.0005 0.0008	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025 0.0057	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006			
2 3 4 5 6 7 8 9 10 11 12 13 14 15	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.0011 0.0011 0.0011 0.0012 0.0017	0.00004 0.00019 0.0006 0.0008 0.0008 0.0009 0.0011	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.0009 0.0009 0.0009 0.001 0.0011	Sb 0.0002 0.0005 0.0007 0.0008 0.0009	Se 0.008 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.0038 0.0032 0.0033 0.0033 0.0034 0.0034 0.0034	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006	Ta 0.0015 0.002 0.0022 0.0001 <0.0001 <0.0001 <0.001 <0.002	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007 0.0007 0.0008	V 0.0001 0.0001 0.0003 0.00038 0.0004 0.0004 0.0005 0.0008	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006 0.001			
2 3 4 5 6 7 8 9 10 11 12 13 14 15 Mean	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.0011 0.0011 0.0011 0.0012 0.0017 0.0043	0.00004 0.00019 0.0006 0.0008 0.00085 0.0009 0.0011	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.00085 0.0009 0.0009 0.0009 0.001	Sb 0.0002 0.0005 0.0007 0.0008 0.0009 0.0035	Se 0.008 <0.0001 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.0028 0.0032 0.0033 0.0034 0.0036 0.00371 0.0045	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006 0.0008	Ta 0.0015 0.002 0.0022 0.0022 0.0001 <0.0001 <0.0001 <0.0002	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007 0.0007 0.0007	V 0.0001 0.0001 0.0003 0.00038 0.0004 0.0004 0.0005 0.0008 0.001	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025 0.0057	Zn 0.00002 0.0001 0.0021 0.0021 <0.0001 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.00042 0.0006 0.001			
2 3 4 5 6 7 8 9 10 11 12 13 14 15 Mean STDV.	0.0007 0.00073 0.0009 0.001 0.001 0.001 0.001 0.0011 0.0011 0.0012 0.0012 0.0013 0.0009	0.00004 0.00019 0.0006 0.0008 0.0008 0.0009 0.0011	0.0005 0.00057 0.0006 0.0006 0.0007 0.0008 0.0009 0.0009 0.0009 0.001 0.0011	Sb 0.0002 0.0005 0.0007 0.0008 0.0009 0.0035	Se 0.008 <0.0001 <0.0001	\$i 0.002 0.002 0.0024 0.0025 0.0028 0.0028 0.0032 0.0033 0.0034 0.0036 0.00371 0.0045	0.0001 0.0002 0.0003 0.0003 0.0005 0.0005 0.0006 0.0008	Ta 0.0015 0.002 0.0022 0.0022 0.0001 <0.0001 <0.0001 <0.0002 0.0002	Ti 0.00006 0.0002 0.0002 0.0003 0.0004 0.0004 0.0005 0.0007 0.0007 0.0008 0.001	V 0.0001 0.0001 0.0003 0.0003 0.0004 0.0005 0.0005 0.0001	W 0.0002 0.001 0.001 0.0011 0.0012 0.0025 0.0057	Zn 0.00002 0.0001 0.0021 <0.0001 <0.0001	Zr 0.0001 0.0002 0.0002 0.0004 0.0004 0.0006 0.001			





Participating Laboratories

ATI Specialty Materials, Lockport ArcelorMittal Dofasco Ellwood National Steel Tata Steel Limited Anderson Laboratories, Inc. Special Metals IncoTest Lockport, NY Hamilton, ON Irvine, PA Jamshedpur, India Greendale, WI Hereford, UK LECO Corporation Laboratory Testing, Inc. Carpenter Technology Corporation Laboratorio Prove Materiali S. Marco srl NSL Analytical Services Dirats Laboratories St. Joseph, MI Hatfield, PA Reading, PA Schio, Italy Cleveland, OH Westfield, MA

Traceability

Members of the "Inter-Laboratory Analysis Program" (ILAP) validate test methods and instrument performance utilizing SRMs, CRMs, and RMs produced by recognized Certifying Bodies. The specific SRMs, CRMs, and RMs applicable to the material covered by this certificate are:

ALPHA AR1648 BCS CRM 13 ALPHA AR556 BCS CRM408/2 ALPHA AR669 BCS CRM456/2 ALPHA AR881 BCS SS451 ALPHA AR892 BCS SS452 ALPHA AR946 BS 60C ASTM 2041 BS HPFE1-13 ASTM 3012 ECRM 097-1 BAM 032-2 EURONORM CRM 097-1 BCS 351 IARM 156A BCS 454/1 IARM 156B BCS 462/1 IARM 27D	IARM 37J IH R5657 LECO 0500-13 LECO 501-550 LECO 501-643 LECO 501-644 LECO 501-644 LECO 501-673 LECO 501-676 LECO 501-902 LECO 502-198	LECO 502-257 LECO 502-348 LECO 502-402 LECO 502-456 LECO 708917409 LECO 762-747 LECO J0487-12 NIST 1227 NIST 1220 NIST 1263A NIST 1265A	NIST 1761A NIST 1762 NIST 1763 NIST 1763A NIST 1764 NIST 1765 NIST 1766 NIST 1767 NIST 1768 NIST 3102A NIST 3109A NIST 3112A	NIST 3114 NIST 3128 NIST 3134 NIST 3137 NIST 3155 NIST 3161A NIST 3162A NIST 3168A NIST 31680 NIST 3169 NIST 361	NIST 36 NIST 36 TH 104
---	--	---	---	--	------------------------------

Homogeneity and Uncertainty

"Uncertainty" values, as reported adjacent to certified concentration values, are based on a 95% Confidence Interval. These estimated uncertainties include the combined effects of method imprecision, material inhomogeneity, and any bias between methods. Homogeneity data from experimental XRF results are reflected in both the overall statistics and certified data. Homogeneity samples are selected by a stratified random sampling procedure. The number of samples may be determined by equation 1, where N_{prod} is the number of units produced and N_{min} is the number of samples used for homogeneity testing. These samples are arranged in a simple randomized design such that each sample is analyzed multiple times by XRF. Homogeneity is also determined within sample using an applied version of ASTM E826. A single factor ANOVA is used to calculated uncertainty due to inhomogeneity (U_{hom}). Uncertainty of the material is calculated by equation 2, where $H=U_{hom}$, S= Standard deviation, t= t-value at 95% CI, and n= number of observations.

1.
$$N_{min} = \max(10, \sqrt[3]{N_{prod}})$$
 2. $U_{CRM} = \frac{\sqrt{H^2 + S^2}}{\sqrt{n}} * t$

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30–1992 list the following:

Certifying Body: Any technically competent body (organization or firm, public or private) that issues a reference material certificate with the information detailed in ISO Guide 31. The only generally accepted certifying body in the United States for primary standards or Standard Reference Materials (SRM) is the U. S. Department of Commerce, National Institute of Standards & Technology (NIST), Gaithersburg, MD. All other certifying bodies in the United States produce Reference Materials (RM) or Certified Reference Materials (CRM).

Reference Material (RM): Material or substance, with one or more property values that are sufficiently homogeneous and well established, to be used for the calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): Reference material, accompanied by a certificate, with one or more property values certified by a procedure, which establishes its traceability to an accurate realization of the unit in which the property values are expressed, and for which each certified value is accompanied by an uncertainty at a stated level of confidence.


Inter-Laboratory Analysis Program (ILAP): ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", but also outlines a well thought out and logical plan for conducting an inter laboratory program involving multiple analytical techniques. Therefore, the guidelines established in ASTM E691-87 were applied to all aspects of this inter laboratory program, including the protocols for planning, handling, analysis and treatment of resulting data.

Methods of Analysis: The "Inter Laboratory Analysis Program" analyzes a wide variety of materials, and as a result, no single analytical method would provide optimum analytical results. Therefore, a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, X-Ray spectrometric, and other accepted methods were used to produce analytical data. Carbon, Sulfur, Nitrogen, and Oxygen results were supplied from combustion and OE instrument procedures.

Expiration of Certification: The certification of this IARM is valid indefinitely, within the uncertainty specified, provided the IARM is handled and stored in accordance with the instructions stated on this certificate. The certification is nullified if the IARM is damaged, contaminated, otherwise modified, or used in a manner for which it was not intended.

Instructions for Use: The test surface is on the side opposite to the labeled surface, which includes the IARM number. The entire thickness of the unit is certified. However, the user is cautioned not to measure disks less than 2 mm thick when using X-ray fluorescence spectrometry. Each packaged disk has been prepared by finishing the test surface using a lathe. The user must determine the correct surface preparation procedure for each analytical technique. The user is cautioned to use care when either resurfacing the disk or performing additional polishing, as these processes may contaminate the surface. The minimum sample size for chips should be individually evaluated based on the analytical technique used; this would typically be greater than 0.1 grams. The material should be stored in a cool, dry location when not in use. Chips are not to be used for Oxygen analysis.

Selection of Materials: A "batch" or "series" is defined as a continuous length of bar produced from a single heat. The majority of IARM materials are in wrought condition; other methods of manufacture are utilized if necessary. ILAP samples are removed from equal sections from the total length of the bar. A portion of each section is converted to chips and a thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis.



David Coler, General Manager

