

# Analytical Reference Materials International

## Certificate of Analysis Certified Reference Material



Grade: NMS J38 / UNS NA

Part Number (Q.A. NO.): IARM 294A

Certificate Date: 04/09/2008

Certificate No.: 294A-04092008-IARM-F

Revision Date: 02/26/2009

### Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
2. Any data reported and enclosed by a **parentheses ( )** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets [ ]** indicates **further testing is in process**.
4. The "**±Estimated Uncertainty**" is enclosed by a **parentheses ( )** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

**Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!**

<u>Aluminum</u> (0.01)	<u>Boron</u> (0.003)	<u>Carbon</u> 0.017 (0.001)	<u>Cobalt</u> 0.021 (0.002)	<u>Chromium</u> 19.7 (0.1)	<u>Copper</u> 0.34 (0.01)	<u>Manganese</u> 21.6 (0.2)
<u>Molybdenum</u> 1.8 (0.04)	<u>Nitrogen</u> 0.78 (0.01)	<u>Niobium</u> 0.03 (0.003)	<u>Nickel</u> 2.9 (0.03)	<u>Oxygen</u> 0.003 (0.001)	<u>Phosphorus</u> 0.026 (0.001)	<u>Sulfur</u> 0.0028 (0.0001)
<u>Silicon</u> 0.43 (0.01)	<u>Tantalum</u> (0.003)	<u>Tin</u> (0.006)	<u>Titanium</u> (0.002)	<u>Vanadium</u> 0.046 (0.001)	<u>Tungsten</u> 0.01 (0.003)	<u>Zirconium</u> (0.002)

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Anderson Laboratories, Inc. - Greendale, WI  
Bodycote Testing - Chicago, IL  
Bodycote Testing - Portland, OR  
Crucible Specialty Metals - Syracuse, NY  
Jorgensen Forge Corp. - Seattle, WA  
Laboratory Testing, Inc. - Hatfield, PA  
Outokumpu Stainless OY - Tornio Finland

ATI Allvac, Lockport - Lockport, NY  
Bodycote Testing - Gary, IN  
Carpenter Technology Corporation - Reading, PA  
IMR Test Labs - Lansing, NY  
Kalco Metals, Inc - Farrell, PA  
Latrobe Specialty Steel Co. - Latrobe, PA

**Traceability:** All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs, and RMs applicable to the material covered by this certificate are: NIST 2159, LECO 502-072, J38, NIST 362, 1233, IARM 27C, 214A, BS 182, IS 0033A, 0035A, 0076A, 0085A, 0145A, LECO 502-072, 502-199, NIST 101E, 160A, 348A, 3101A, 3102A, 3103A, 3106, 3109A, 3128, 3131A, 3137, 3149, 3155, 3161A, 3162A, 3163, 3165, 3168A, 3169, IARM 19B, MBH 13XNS01A, CMSI 1358, LECO 501-644, 502-016, ALPHA AR881, NIST 160B, 362, BCS 464/1, LECO 501-502, 501-645, BS 182, 190, 191, LECO 501-679, 502-016, 502-072, 999-085, IARM 214A, BS 190, LECO 502-072, NIST 1233, IARM 17B, 19B, 214A, BS 182, LECO 501-674, 502-072, NIST 1297, BS 180, 182, 1233, IARM 17C, 214A, LECO 501-501, 502-016, ALPHA AR 890, 892, IARM 17C, 18B, 19B, 214A, IARM 214A, BS 180A, ALPHA AR663, AR881, LECO 501-502, IARM 214A, MBH 13XNSD1A, 13XNSD1B.

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

**See Reverse Side for Statistical Data and Additional Information Regarding this Material.**

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 02/26/2009.

294A	Al	B	C	Co	Cr	Cu	Mn	Mo	N	Nb	Ni	O	P	S	Se
1	0.0124	0.0059	0.0164	0.0176	19.55	0.300	22.08	1.74	0.819	0.0391	2.92	0.0030	0.0221	0.00300	0.0045
2	0.001	0.0050	0.0205	0.022	19.70	0.379	21.76	1.76	0.775	0.025	2.935	0.0052	0.023	0.003	<0.01
3	0.0037	0.00352	0.0160	0.0154	19.93	0.336	21.354	1.805	0.767	0.0275	2.963	0.0035	0.0282	0.0028	<0.00003
4	0.0192	0.0037	0.0170	0.0225	19.733	0.341	21.568	1.801	0.8104	0.0302	2.971	0.0033	0.0258	0.0028	<0.0025
5	0.0010	0.0019	0.0161	0.0213	19.614	0.3393	21.812	1.78	0.7862	0.0325	2.95	0.0024	0.0254	0.0025	
6	0.0067	0.002567	0.0166	0.0168	19.82	0.354	22.06	1.81	0.7576	0.027	2.967	0.00075	0.0319	0.0029	
7	0.0070	0.00263	0.0168	0.020467	19.466	0.3211	21.62	1.741	0.7958	0.02773	2.874	0.0024	0.023	0.00249	
8	0.00497	0.0035	0.0173	0.0294	19.848	0.342	21.698	1.841	0.7555	0.0293	2.924	0.00317	0.0278	0.00275	
9	0.0178	0.0035	0.0190	0.0248	19.88	0.365	21.34	1.831	0.7685	0.0373	2.92	0.0032	0.0288	0.0028	
10	0.0049	0.0037	0.0196	0.023	19.729	0.325	21.230	1.70	0.7607	0.037	2.830		0.0253	0.0025	
11	0.0078		0.0177	0.0202	19.705	0.3551	21.868	1.890	0.791	0.0379	2.888		0.0281	0.0026	
12			0.0183	0.0188	19.584	0.345	20.970	1.792	0.7526	0.0328	2.901		0.0253	0.0030	
13			0.016	0.0270		0.3370	21.523	1.7993	0.806	0.0259	2.890		0.0244		
14			0.0170	0.020		0.309		1.660		0.041	2.837		0.027		
15				0.0218		0.3366		1.624		0.0285			0.0240		
Mean	0.0079	0.0036	0.0175	0.0214	19.7133	0.3390	21.6064	1.7716	0.7804	0.0319	2.9121	0.0030	0.0260	0.0028	0.0045
STDV.	0.0062	0.0013	0.0014	0.0037	0.1413	0.0203	0.3244	0.0700	0.0225	0.0053	0.0450	0.0012	0.0026	0.0002	
Certified (0.01)	(0.003)	0.017	0.021	19.7	0.34	21.6	1.8	0.78	0.03	2.9	0.003	0.026	0.0028		
95% C.I.		0.001	0.002	0.1	0.01	0.2	0.04	0.01	0.003	0.03	0.001	0.001	0.001		
Methods	X,I,O	I,O	C,O	X,I,O	X,W,I,O	X,I,O	X,I,O	X,I,O	F,O	X,I,O	X,W,I,O	F	X,I,O	X,C,O	

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

294A	Si	Sn	Ta	Ti	V	W	Fe	As	Bi	Ca	Sb	Mg	Pb	Zn	Zr
1	0.381	0.00290	0.0030	0.002	0.0484	0.00872	52.72	0.00593	0.00058	0.0019	0.0015	0.0007	0.00050	0.00406	0.0012
2	0.410	0.008	0.0035	0.0022	0.049	0.0220		0.001	0.0004	0.0017	<0.0001		0.0008	0.004	0.0014
3	0.413	0.0073	0.004	0.0030	0.0422	0.0112		0.0022	<0.0010	0.0010	0.0030		0.0008	<0.0010	0.0017
4	0.421	0.0052	0.0030	0.0042	0.0469	0.0107		0.0064	<0.00003				0.0007		0.0036
5	0.449	0.0047		0.001	0.0471	0.0150			<0.0010				0.0009		0.0040
6	0.411	0.009		0.000667	0.0466	0.015									
7	0.4160	0.0050		0.0021	0.045	0.008									
8	0.449	0.0038		0.0028	0.044	0.0185									
9	0.417	0.0077		0.0030	0.0441	0.0091									
10	0.453	0.0017		0.0028	0.0459	0.0119									
11	0.4363	0.0039		0.0020	0.048	0.0168									
12	0.446	0.0084		0.0029	0.0461										
13	0.4147	0.0059													
14	0.4340	0.0046													
Mean	0.4251	0.0055	0.0034	0.0024	0.0461	0.0134	52.7200	0.0039	0.0005	0.0015	0.0023	0.0007	0.0007	0.0040	0.0024
STDV.	0.0203	0.0022	0.0005	0.0010	0.0020	0.0045		0.0027	0.0001	0.0005	0.0011		0.0002	0.0000	0.0013
Certified	0.43	(0.006)	(0.003)	(0.002)	0.046	0.01							(0.001)		(0.002)
95% C.I.	0.01				0.001	0.003									
Methods	X,W,I,O	X,I,O	X,I,O	X,I,O	X,I,O	X,I,O							X,I,O		X,I,O

Legend: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS, H = Hollow Cathode OE

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1992 list the following:

**Certifying Body:** Any technically competent body (organization or firm, public or private) that issues a reference material certificate which provides the information detailed in ISO Guide 31. The only generally accepted certifying body in the United States for primary standards - Standard Reference Materials (SRM) is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD. All other certifying bodies in the United States produce Reference Materials (RM) or Certified Reference Materials (CRM).


**Reference Material (RM):** Material or substance one or more of whose property values are sufficiently homogeneous and well established to be used for the calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

**Certified Reference Material (CRM):** Reference material, accompanied by a certificate, one or more of whose property values are certified by a procedure which establishes its traceability to an accurate realization of the unit in which the property values are expressed, and for which each certified value is accompanied by an uncertainty at a stated level of confidence.

**Inter-Laboratory Analysis Program (ILAP):** Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

**Methods of Analysis:** In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission, and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

**Selection of Materials:** A "batch" or "series" is defined as a single bar of one continuous length and heat. The majority of materials are in wrought condition; other methods of manufacture are utilized as a less desirable resort. ILAP samples are taken by removing a section, a minimum of, every one-twelfth of total length from the entire bar. A portion of the section is converted to chips and thin (pin) disk for analysis by classical wet chemistry, ICP, AA, and combustion procedures, and the balance remains as a thick disk for OES and X-Ray analysis. Each member of the ILAP is furnished a sample pack from a specific location on the batch bar. This systematic sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data. This method of homogeneity testing is in accordance with ISO Guide 34, regarding the systematic selection and testing of a representative number of units for the assessment of homogeneity.

Certified by:   
 William D. Britt, President/General Manager  
 Analytical Reference Materials International

Certificate No.: 294A-04092008-IARM-F  
 Certificate Date: 04/09/2008  
 Revision Date/No.: 02/26/2009