

# Analytical Reference Materials International

## Certificate of Analysis Certified Reference Material



Grade: **AISI 4620 / UNS G46200**

Part Number (Q.A. NO.): **IARM 33C**

Certification Date: **10/06/1999**

Certificate No.: **33C-10061999-IARM-F**

Revision Date: **05/19/2003**

### Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community.
2. Any data reported and enclosed by a **parentheses ( )** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets [ ]** indicates **further testing is in process**.
4. The "**± Confidence Interval at 95%**" is enclosed by a **parentheses ( )** below the individual element's concentration.

**IMPORTANT:** A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Aluminum</u> 0.025 (0.0005)	<u>Antimony</u> 0.025 (0.0005)	<u>Arsenic</u> (0.005)	<u>Boron</u> (0.0002)	<u>Calcium</u> (0.0003)	<u>Carbon</u> 0.184 (0.001)	<u>Chromium</u> 0.133 (0.003)	<u>Cobalt</u> 0.008 (0.001)
<u>Copper</u> 0.223 (0.002)	<u>Lead</u> <0.002	<u>Manganese</u> 0.562 (0.006)	<u>Molybdenum</u> 0.236 (0.004)	<u>Nickel</u> 1.71 (0.01)	<u>Niobium</u> 0.002 (0.001)	<u>Nitrogen</u> 0.0078 (0.0002)	<u>Oxygen</u> 0.0021 (0.0005)
<u>Phosphorus</u> 0.009 (0.001)	<u>Sulfur</u> 0.017 (0.001)	<u>Silicon</u> 0.25 (0.01)	<u>Tin</u> 0.009 (0.001)	<u>Titanium</u> 0.0014 (0.0004)	<u>Tungsten</u> 0.0026 (0.0008)	<u>Vanadium</u> 0.0021 (0.0006)	<u>Zirconium</u> 0.0021 (0.0006)

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

AK Steel, Butler Works - Butler, PA	Algoma Steel Corp. - Sault Ste. Marie, Ontario, Canada
Allegheny Ludlum Corp. - Brackenridge, PA	Anderson Laboratories, Inc. - Greendale, WI
Bodycote Metal Analysis, Inc. - Santa Fe Springs, CA	Dofasco Inc. - Hamilton, Ontario, Canada
International Steel Group - East Chicago, IN	Koppel Steel - Koppel, PA
Laboratory Testing, Inc. - Hatfield, PA	National Steel-Great Lakes Operations - Ecorse, MI
The Timken Company - Canton, OH	The Timken Company - Canton, OH

**Traceability:** All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs and RMs applicable to the material covered by this certificate are: NBS 1164, IARM 95A, 94A, NIST 1761, 1762, 1763, 1764, 1765, 1766, 1767, 1262, 1263, 1264, 1265, 1754, 1136, 1161, 1162, 1163, 1164, 1165, 1166, 1167, 1168, 16F, 361, 362, 364, 365, NIST 32e, 73c, BS 59c, LECO 501-679, 501-550, NIST 293, 11H, LECO 501-644, 501-643, TPBN-250, TSNH-500, TWNF-250, TBIN-250, TCAN-500, TMGN-500, TSEN-100, TTAF-250, TZNN-500, TZRN-250, NIST 1761, 1762, 1763, 1764, 1765, 1766, 1767, 2166, 12H, LECO 501-504, 501-552, 501-550, NIST 1761, 1762, 1763, 1764, 1765, 1766, 1767, NIST 1761, 1762, 1763, 1764, 1765, 1766, 1767, BS 3841, IARM 31B, CarTech 051, LECO 501-644, NBS 361, 362, 363, 152A, IARM 30B, LECO 501-677, NIST 361, 363, 1761, 1764, 1766, 139B, 368, 14F, ST626, EURO 031-3, LECO 501-643, NIST 1136, 1161, 1162, 1163, 1164, 1165, 1166, 1167, 1168, 1173, 1254, 1261, 1262, 1263, 1264, 1265, 1761, 1762, 1763, 1764, 1765, 1766, 1767, CA-1-CA-5, JSS 150/6-155/6, 168/4-175/4, 190-195, BAS H/1 B/3, C/8, D/8, SUS RE1212

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

**See Reverse Side for Statistical Data and Additional Information Regarding this Material.**

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 05/19/2003.

33C	Al	B	C	Co	Cr	Cu	Mn	Mo	N	Nb	Ni	O	P	Pb	S
1	0.0246	0.00013	0.187	0.006	0.138	0.220	0.55	0.232	0.00769	0.002	1.72	0.0018	0.011	<0.0004	0.016
2	0.025	<0.0005	0.185	0.0081	0.134	0.228	0.55	0.236	0.00715	0.001	1.713	0.0020	0.010	0.0013	0.0173
3	0.0259	0.0004	0.1795	0.0067	0.1359	0.228	0.563	0.2272	0.0078	0.0007	1.701	0.0028	0.008	0.0002	0.0147
4	0.025	0.00009	0.182	0.009	0.135	0.224	0.567	0.244	0.0080	0.002	1.706	0.0027	0.0094		0.0181
5	0.0243	0.00013	0.185	0.00780	0.135	0.220	0.5683	0.234	0.0082	0.001	1.699	0.0010	0.0116		0.0179
6	0.0245	0.00025	0.186	0.0095	0.136	0.224	0.568	0.242	0.0084	0.0030	1.725	0.00228	0.009		0.0183
7	0.026	<0.0006	0.1824	0.008	0.1265	0.2210	0.565	0.2350	0.00777	0.0026	1.713	0.00176	0.010		0.0175
8	0.0252	0.00006	0.1865		0.133	0.221	0.558	0.231	0.0075	0.0024	1.7060	0.0025	0.008		0.0177
9	0.0255		0.1846		0.131	0.2219	0.5523	0.2469	0.00789	0.00216	1.69		0.008		0.017
10	0.024		0.183		0.126	0.229	0.567	0.232	0.00786		1.71		0.0085		0.01723
11			0.1837		0.13663	0.2191	0.584	0.23531	0.00789		1.714		0.00826		0.0179
12							0.567				1.7212		0.009		0.0162
13							0.54747						0.00726		
Mean	0.0250	0.0002	0.1841	0.0079	0.1334	0.2233	0.5621	0.2359	0.0078	0.0019	1.7099	0.0021	0.0091	0.0008	0.0172
STDV.	0.0007	0.0001	0.0022	0.0012	0.0040	0.0036	0.0102	0.0060	0.0003	0.0008	0.0101	0.0006	0.0013	0.0008	0.0010
Certified	0.025	(0.0002)	0.184	0.008	0.133	0.223	0.562	0.236	0.0078	0.002	1.71	0.0021	0.009	<0.002	0.017
95% C.I.	0.0005		0.001	0.001	0.003	0.002	0.006	0.004	0.0002	0.001	0.01	0.0005	0.001		0.001
Methods	I,O	I,O	C,O	X,I,O	X,I,O	X,O	X,I,O	X,I,O	F,O	X,I,O	X,I,O	F	X,I,O	X,D,A	C,O

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G=GDMS

33C	Si	Sn	Ti	V	W	As	Bi	Ca	Cd	Mg	Sb	Se	Ta	Zn	Zr
1	0.22	0.0102	0.002	0.0022	0.0026	0.0042	<0.0001	0.0005	<0.0001	0.0008	0.0022	0.0029	0.0031	0.002	0.00060
2	0.27	0.010	0.0011	0.0035	0.002	0.0048	<0.001	0.00029	0.0001	0.001	0.00160	0.004	0.00390	<0.0001	<0.001
3	0.246	0.0080	0.001	0.0019	0.0021	0.0039		0.000306		<0.01			0.001	0.001	
4	0.251	0.009	0.0005	0.001	0.004	0.0043		<0.0005						0.00233	
5	0.264	0.0083	0.001	0.001	0.002	<0.01		0.00026						0.0028	
6	0.231	0.00930	0.001	0.001	0.00270	0.00535								0.00015	
7	0.26	0.0088	0.00190	0.00260											
8	0.245	0.00981	0.0021	0.0024											
9	0.2375	0.009	0.00197	0.00236											
10	0.242	0.0092	0.00171	0.003											
11	0.2507			0.00259											
12	0.253														
13	0.23714														
Mean	0.2467	0.0092	0.0014	0.0021	0.0026	0.0045	#DIV/0!	0.0003	0.0001	0.0009	0.0019	0.0035	0.0027	0.0017	0.0006
STDV.	0.0137	0.0007	0.0006	0.0008	0.0008	0.0006	#DIV/0!	0.0001	#DIV/0!	0.0001	0.0004	0.0008	0.0015	0.0011	#DIV/0!
Certified	0.25	0.009	0.0014	0.0021	0.0026	(0.005)		(0.0003)						(0.002)	
95% C.I.	0.01	0.001	0.0004	0.0006	0.0008										
Methods	X,I,O	X,A,O	X,I,O	X,I,O	X,I,O	D,A,O		I,O						D,I,O	

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G=GDMS

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981-(E) list the following:

**Certifying Body:** A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.


**Reference Material (RM):** A material or substance with one or more properties which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

**Certified Reference Material (CRM):** A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

**Inter-Laboratory Analysis Program (ILAP):** Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

**Methods of Analysis:** In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen and Oxygen are the result of combustion instrument procedures.

**Selection of Materials:** A "batch" or "series" is defined as a single bar of one continuous length. The majority of materials are in wrought condition. Other methods of manufacture are utilized as a last resort, only in the case of those materials being unavailable in wrought condition. "Batch" samples are taken by removing a one-inch cross section for every thirteen inches of total length from the entire bar. Twenty-five percent of the one inch cross section is converted to chips for analysis by classical wet chemistry, ICP, AA, and combustion procedures and seventy-five percent remains in a solid disk form for OES and X-Ray analysis where applicable. Each member of the ILAP is furnished both a solid sample and the corresponding supply of chips from a specific location on the batch bar. This massive sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data.

Certified by:   
 William D. Britt, President/General Manager  
 Analytical Reference Materials International

Certificate No.: 33C-10061999-ARM-F  
 Certification Date: 10/06/1999  
 Revision Date/No.: 05/19/2003