

Analytical Reference Materials International

Certificate of Analysis Certified Reference Material



Grade: **AISI 321 / UNS S32100**

Part Number (Q.A. NO.): **IARM 6E**

Certification Date: **03/30/2004**

Certificate No.: **6E-03302004-IARM-F**

Revision Date: **03/30/2004**

Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community.
2. Any data reported and enclosed by a **parentheses ()** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets []** indicates **further testing is in process**.
4. The **"±Estimated Uncertainty"** is enclosed by a **parentheses ()** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Aluminum</u> 0.139 (0.004)	<u>Boron</u> 0.0005 (0.0002)	<u>Carbon</u> 0.046 (0.001)	<u>Cobalt</u> 0.148 (0.002)	<u>Chromium</u> 17.25 (0.02)	<u>Copper</u> 0.238 (0.003)	<u>Manganese</u> 1.67 (0.01)
<u>Molybdenum</u> 0.383 (0.004)	<u>Nitrogen</u> 0.011 (0.001)	<u>Niobium</u> 0.048 (0.002)	<u>Nickel</u> 10.49 (0.02)	<u>Oxygen</u> 0.0011 (0.0003)	<u>Phosphorus</u> 0.023 (0.001)	<u>Sulfur</u> 0.022 (0.001)
<u>Silicon</u> 0.489 (0.004)	<u>Tantalum</u>	<u>Tin</u> 0.007 (0.001)	<u>Titanium</u> 0.49 (0.01)	<u>Vanadium</u> 0.144 (0.002)	<u>Tungsten</u> 0.029 (0.004)	<u>Zirconium</u> (0.001)

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Allegheny Ludlum Corp. - Brackenridge, PA
Anderson Laboratories, Inc. - Greendale, WI
Crucible Specialty Metals - Syracuse, NY
Koppel Steel - Koppel, PA
MetalTek International, Inc. - Waukesha, WI
The Timken Company - Canton, OH

Allvac - Monroe, NC
Carpenter Technology Corporation - Reading, PA
IMR Test Labs - Lansing, NY
Laboratory Testing, Inc. - Hatfield, PA
Special Metals Corporation - Huntington, WV
Timken Latrobe Steel Co. - Latrobe, PA

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs, and RMs applicable to the material covered by this certificate are: BS 85D, IARM 6B, BS 81T, LECO 501-644, NIST 362, IARM 6A, 27C, BS 85D, IC 14991, LECO 501-647, NIST 73c, 121d, 885, LECO 501-503, 501-553, 501-643, 501-644, Alpha AR512, NIST 1761, 1762, 1763, 1764, 1765, 1766, 1767, 1261, 1262, 1263, 1264, 1265, 344, 362, BS 321C, LECO 501-551, 501-553, NIST 1157, 1158, 1171, 1247, 1286, 1287, 1295, 1754, 2171, 3103A, 3155, 3163, 3169, BS 321A, 321C, IARM 6B, 6C, LECO 501-501, 501-553, 501-550, NIST 1760, 1761, 1762, 1763, 1764, 1765, 1766, 1767, 337A, C1151, C1152, C1153, C1154, C1287, 1171, 1172, 1754, 1160, 1161, 1162, 1163, 1164, 1261A, JSS 168-4, 169-4, 170-4, 171-4, 172-4, 173-4, 174-4, 175-4, ST01, ST02, ST03, ST04, ST05, ST06, BAS SS401/1, 402/1, 403/1, 404/1, 405/1, 406/1, 407/1, 408/2, 409/1, 410/2, L469, 470, 471, 472, 473, 474, 475, LECO 501-510, 501-645, BS 14, 14B, XEEH, XAAS, XCCV, XCCS, CA-1, CA-2, CA-3, CA-4, CA-1A, CA-3A, NIST 121D, 160A, 339, 344, IARM 6B, 6C, 15B, LECO 501-502, 501-553, BS 321C, NIST 3107A, 3155, 3161A, IARM 2A, 2C, 1A, 6A, 6B, 8A, 8B, BS 9941, 9942LECO 501-504, 501-676, 501-674, 501-647, 501-644, 501-643, 501-646, NIST 131G, HAS 600C, 321A, 805B, 400M, 25-6A, LECO 502-256, 501-550, IARM 6C, 6A

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

700 Corporate Cr., Suite A · Golden, Colorado 80401 · Telephone (303) 216-2621 · FAX (303) 216-2649

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 03/30/2004.

6E	Al	B	C	Co	Cr	Cu	Mn	Mo	N	Nb	Ni	O	P	S	Se
1	0.140	0.0008	0.048	0.150	17.25	0.240	1.67	0.390	0.0110	0.050	10.50	0.0008	0.023	0.026	<0.0001
2	0.1433	0.0008	0.044	0.1523	17.23	0.230	1.68	0.380	0.0104	0.0468	10.56	0.00073	0.024	0.021	0.001
3	0.137	0.0006	0.0443	0.150	17.24	0.248	1.690	0.394	0.0098	0.049	10.44	0.0011	0.0243	0.0202	<0.0001
4	0.1358	0.00025	0.0443	0.1491	17.279	0.243	1.671	0.383	0.0106	0.0453	10.482	0.00070	0.0228	0.0224	
5	0.1423	0.00025	0.0483	0.148	17.21	0.2461	1.717	0.3941	0.0093	0.047	10.514	0.00093	0.0210	0.0200	
6	0.148	0.00045	0.0455	0.146	17.21	0.234	1.653	0.384	0.0104	0.0422	10.528	0.00122	0.0221	0.0225	
7	0.138	0.0005	0.044	0.145	17.290	0.239	1.67	0.371	0.0102	0.048	10.51	0.001433	0.0214	0.0241	
8	0.139	0.0004	0.046	0.149	17.21	0.234	1.680	0.381	0.01274	0.050	10.480	0.0016	0.021	0.024	
9	0.1479	0.0004	0.047	0.150933	17.28	0.238	1.67	0.376	0.0116	0.044	10.52		0.023	0.020	
10	0.130		0.04755	0.148	17.303	0.240	1.69	0.391	0.011167	0.0522	10.48		0.0228	0.024	
11	0.1275		0.044	0.148	17.302	0.23615	1.635	0.3775	0.0132	0.048	10.42025		0.02245	0.0226	
12			0.044	0.1439	17.19	0.236	1.654	0.390	0.0124	0.045	10.485		0.0242	0.0218	
13			0.0448		17.22	0.239	1.65	0.374		0.0506	10.47		0.022	0.022	
14						0.2357	1.690	0.3811			10.43		0.0214		
Mean	0.1384	0.0005	0.0451	0.1492	17.2384	0.2385	1.6729	0.3833	0.0126	0.0475	10.4871	0.0019	0.0225	0.0216	0.0010
STDV.	0.0142	0.0002	0.0022	0.0038	0.0501	0.0049	0.0209	0.0075	0.0040	0.0029	0.0391	0.0014	0.0011	0.0035	
Certified	0.139	0.0005	0.046	0.148	17.25	0.238	1.67	0.383	0.011	0.048	10.49	0.0011	0.023	0.022	
95% C.I.	0.004	0.0002	0.001	0.002	0.02	0.003	0.01	0.004	0.001	0.002	0.02	0.0003	0.001	0.001	
Methods	X,I,O	I,O	C,O	X,A,I,O	X,A,O	X,A,I,O	X,A,I,O	X,A,I,O	F	X,A,I,O	X,W,A,O	F	X,I,O	X,C,O	

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G=GDMS

6E	Si	Sn	Ta	Ti	V	W	Ag	As	Bi	Ca	H	Mg	Pb	Te	Zr
1	0.490	0.0080	0.0062	0.48	0.140	0.032	0.0004	0.0027	0.0002	0.0005		0.0010	0.0002	0.0004	0.0006
2	0.500	0.0070	0.0073	0.46	0.1435	0.0273	0.00013	0.0038	<0.001	0.0002		<0.001	0.0002	<0.0001	0.0014
3	0.482	0.0073	0.0206	0.482	0.144	0.023		0.0035	<0.00001	0.0002		0.0001	0.00025		0.00052
4	0.484	0.0066	<0.001	0.490	0.1427	0.0286		0.0040					0.0004		0.001
5	0.4931	0.0055	0.001	0.5036	0.143	0.018		0.0026							0.002
6	0.496	0.0070	0.0025	0.485	0.147	0.033									0.0012
7	0.497	0.0050	0.03375	0.478	0.145	0.037									
8	0.485	0.0076	<0.001	0.497	0.1450	0.036									
9	0.492	0.00728	0.0010	0.494	0.149	0.026333									
10	0.495	0.0080	0.0181	0.509	0.141567	0.027									
11	0.4817	0.0062		0.507	0.141	0.025									
12	0.481	0.0056		0.478	0.148	0.0335									
13	0.4856			0.492	0.1461										
14				0.508											
Mean	0.4911	0.0064	0.0113	0.4903	0.1443	0.0304	0.0003	0.0034	0.0002	0.0038		0.0006	0.0002	0.0004	0.0015
STDV.	0.0089	0.0015	0.0118	0.0142	0.0027	0.0077	0.0002	0.0016		0.0069		0.0006	0.0002	0.0001	0.0011
Certified	0.489	0.007		0.49	0.144	0.029		(0.003)		(0.0003)			(0.0002)		(0.001)
95% C.I.	0.004	0.001		0.01	0.002	0.004									
Methods	X,W,A,O	X,I,O	I,O	X,I,O	X,I,O	X,I,O		A,I,O		I,O				D,A,I,O	X,I,O

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G=GDMS

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981-(E) list the following:

Certifying Body: A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.


Reference Material (RM): A material or substance with one or more properties which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

Methods of Analysis: In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length. The majority of materials are in wrought condition. Other methods of manufacture are utilized as a last resort, only in the case of those materials being unavailable in wrought condition. "Batch" samples are taken by removing a one-inch cross section for every thirteen inches of total length from the entire bar. Twenty-five percent of the one inch cross section is converted to chips for analysis by classical wet chemistry, ICP, AA, and combustion procedures and seventy-five percent remains in a solid disk form for OES and X-Ray analysis where applicable. Each member of the ILAP is furnished both a solid sample and the corresponding supply of chips from a specific location on the batch bar. This massive sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data.

Certified by: 
 William D. Britt, President/General Manager
 Analytical Reference Materials International

Certificate No.: 6E-03302004-ARM-F
 Certification Date: 03/30/2004
 Revision Date/No.: 03/30/2004