

Analytical Reference Materials International

Certificate of Analysis Certified Reference Material



Grade: **CDA 675 / UNS C67500**

Part Number (Q.A. NO.): **IARM 83B**

Certification Date: **01/09/2002**

Certificate No.: **83B-01092002-IARM-F**

Revision Date: **04/13/2004**

Interpretation of Data

1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community.
2. Any data reported and enclosed by a **parentheses ()** is a **"best estimate"** and is **NOT CERTIFIED**. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets []** indicates **further testing is in process**.
4. The **"±Estimated Uncertainty"** is enclosed by a **parentheses ()** below the individual **element's concentration** and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

<u>Silver</u> (0.002)	<u>Aluminum</u> 0.002 (0.001)	<u>Antimony</u> (0.004)	<u>Arsenic</u>	<u>Beryllium</u>	<u>Bismuth</u>	<u>Carbon</u> 0.003 (0.0003)
<u>Cobalt</u> (0.003)	<u>Chromium</u> (0.003)	<u>Copper</u> 58.7 (0.2)	<u>Iron</u> 0.97 (0.03)	<u>Manganese</u> 0.13 (0.003)	<u>Nickel</u> 0.010 (0.003)	<u>Phosphorus</u> 0.004 (0.001)
<u>Lead</u> 0.017 (0.003)	<u>Sulfur</u> (0.001)	<u>Selenium</u>	<u>Silicon</u> (0.003)	<u>Tin</u> 0.85 (0.02)	<u>Zinc</u> 39.3 (0.1)	

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Anderson Laboratories, Inc. - Greendale, WI	Bodycote Taussig, Inc. - Skokie, IL
I. Schumann & Company - Bedford, OH	Laboratory Testing, Inc. - Hatfield, PA
MetalTek International, Inc. - Waukesha, WI	Rautaruukki Steel - Raabe, Finland
Riverside Brass & Aluminum Foundry Ltd. - New Hamburg, Ontario, Canada	Sipi-Metals Corp - Chicago, IL
Special Metals Wiggins LTD. - Hereford, England	Spectrochemical Laboratories, Inc. - Pittsburgh, PA
Staveley Services Materials Testing - Gary, IN	The Ingot Co. - Weston, Ontario, Canada

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs and RMs applicable to the material covered by this certificate are: NIST 1104, 1776, 1777, 1778, 1780, IARM 73A, 83A, 87A, 88A, BS 863A, MNB4, NIST 1101, 1119, BNF 50X31, 52X54, 65X17, MBH 11224, AR 673, TH 1045, EU 057-2, BCS 183/1, 390, 304/1, 179/2, 351, 462-1, LECO 501-503, 501-147, 501-102, 501-551, 501-553, NIST 1103, IARM 202A, BCS 304/1, 207, 183/4, LECO 501-644, ALPHA AR881, IARM 83A, LECO 501-550, 502-148, NIST 37D, 1101, BCS 179/2, 390, BAM 222, IARM 151A, 83A, MBH 178700, NIST 62D, 3101A, 3105A, 3106, 3126, 3132, 3150, 3161A, MBH 17870, 17866, NIST 62D, 63C, 158A, 164A, 184, 393, 872, 1121, 1276, IARM 72A, 79A, 81A, 91B, 93B, LECO 502-148, 501-644, NIST 124D, 37E, BCS 179/2, U235, CC865, 857A, L2, C30.21, 485, LH5, U253, NIST 37D, 62C, IARM 83A, NIST C1253, IARM 83A, 75A, BS 464A, LECO 502-148, NIST 1107, BS CC865

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 04/13/2004.

83B	Ag	Al	As	Be	Bi	C	Co	Cr	Cu	Fe	Mn	Ni	P	Pb	S
1	<0.001	0.0024	0.008	<0.001	0.009	0.003	0.005	0.003	58.44	1.01	0.13	0.010	0.0041	0.021	0.0024
2	0.0008	0.002	<0.01	<0.001	<0.01	0.0022	0.0018	0.0007	58.9	0.92	0.135	0.0094	0.0025	0.012	0.0001
3	0.005	0.0033	0.0013	<0.0001	0.0001	0.0025	0.001	0.005	58.6	1.00	0.135	0.007	0.0035	0.01	<0.001
4	0.001	0.0015	<0.01	<0.003	<0.001	0.003	0.004	0.002	58.95	0.925	0.134	0.016	0.003	0.0210	0.0001
5	0.004	0.001	<0.0001	0.0003	0.002	0.002			58.73	1.010	0.138	0.007	0.0032	0.018	0.0018
6	0.0013	0.0013	0.0006		0.0003	0.0027			58.62	1.03	0.142	0.0094	0.0035	0.021	0.001
7		0.0021	0.0054		0.004	0.0025			58.41	0.94	0.13	0.013	0.0047	0.021	0.0001
8					<0.0001				58.638	0.95	0.14	0.017		0.014	0.0013
9									0.99	0.136	0.007			0.0235	0.0016
10									0.975	0.1295				0.012	
11									0.873	0.136				0.0233	
12									0.981	0.1377				0.016	
13									1.017						
Mean	0.0024	0.0019	0.0038	0.0003	0.0031	0.0026	0.0030	0.0027	58.6610	0.9708	0.1353	0.0106	0.0035	0.0177	0.0011
STDV.	0.0019	0.0008	0.0035		0.0037	0.0004	0.0019	0.0018	0.1939	0.0463	0.0040	0.0038	0.0007	0.0048	0.0009
Certified	(0.002)	0.002				0.003	(0.003)	(0.003)	58.7	0.97	0.13	0.010	0.004	0.017	(0.001)
95% C.I.		0.001				0.0003			0.2	0.03	0.003	0.003	0.001	0.003	
Methods	X,I	X,D,I,O				C,O	X,I,O	X,I,O	X,W,A,I	X,A,I,O	X,I,O	X,A,I,O	X,I,O	X,A,I,O	C,I,O

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS

83B	Sb	Si	Sn	Zn	Cd	Mg	Mo	O	Zr	N	B	Ti	Te	Se
1	0.002	0.001	0.870	39.34	0.0048	<0.001	<0.01	<0.001	0.001	<0.001	0.0016	0.001	<0.001	0.01
2	<0.005	<0.01	0.818	39.1	<0.01	<0.001	<0.0001	0.00063	<0.01	<0.0001	<0.01	<0.01		<0.0001
3	0.0013	0.0010	0.88	39.45	0.003	0.0009		0.0028	<0.0001	0.0004	0.0004	0.0003		<0.0001
4	0.003	0.005	0.865	39.310	0.004	0.001		0.0011	<0.01	0.0005				
5	0.007	0.002	0.843	39.25	0.0013	<0.002		0.001	0.0002	<0.001				
6	0.002	0.003	0.82	39.36		0.001			<0.001					
7	<0.0010	0.004	0.82	39.55										
8	0.009	<0.003	0.81	39.34										
9		0.0025	0.905	39.321										
10			0.843	39.17										
11			0.861											
12			0.871											
13			0.827											
Mean	0.0041	0.0026	0.8487	39.3191	0.0033	0.0010		0.0014	0.0006	0.0005	0.0010	0.0007		0.0100
STDV.	0.0032	0.0015	0.0291	0.1283	0.0015	0.0001		0.0010	0.0006	0.0001	0.0008	0.0005		
Certified	(0.004)	(0.003)	0.85	39.3	(0.003)	(0.001)		(0.001)						
95% C.I.			0.02	0.1										
Methods	X,A,I,O	D,I,O	X,A,I,O	X,A,I,O	D,I,O	X,D,I,O		F						

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G = GDMS

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981-(E) list the following:

Certifying Body: A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.


Reference Material (RM): A material or substance with one or more properties which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

Certified Reference Material (CRM): A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

Inter-Laboratory Analysis Program (ILAP): Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

Methods of Analysis: In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen and Oxygen are the result of combustion instrument procedures.

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length. The majority of materials are in wrought condition. Other methods of manufacture are utilized as a last resort, only in the case of those materials being unavailable in wrought condition. "Batch" samples are taken by removing a one-inch cross section for every thirteen inches of total length from the entire bar. Twenty-five percent of the one inch cross section is converted to chips for analysis by classical wet chemistry, ICP, AA, and combustion procedures and seventy-five percent remains in a solid disk form for OES and X-Ray analysis where applicable. Each member of the ILAP is furnished both a solid sample and the corresponding supply of chips from a specific location on the batch bar. This massive sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data.

Certified by: 
 William D. Britt, President/General Manager
 Analytical Reference Materials International

Certificate No.: 83B-01092002-ARM-F
 Certification Date: 01/09/2002
 Revision Date/No.: 04/13/2004