## Analytical Reference Materials International

## Certificate of Analysis Certified Reference Material



Grade: CDA 706 / UNS C70600

Part Number (Q.A. NO.): IARM 84B

Certification Date: **03/19/1999** Certificate No.: **84B-03191999-IARM-F** Revision Date: **06/15/2004** 

## **Interpretation of Data**

- 1. Certified values listed below reflect analysis results submitted by qualified analytical laboratories using a combination of methods and instrumentation that emulate actual methods and instrumental techniques currently utilized in the analytical community and are reported as % wt. unless otherwise noted.
- 2. Any data reported and enclosed by a **parentheses** ( ) is a "best estimate" and is NOT CERTIFIED. This data could not be quantified sufficiently for certification. It was however, reported by enough laboratories to be considered as potentially present in the matrix of the material being examined.
- 3. The "Inter-laboratory Analysis Program" (ILAP) utilized in the establishment of the data are an ongoing program with permanent membership. Certain elements may be selected by a consensus of the members for more extensive testing. Therefore the data in **brackets** [ ] **indicates further testing is in process.**
- 4. The "±Estimated Uncertainty" is enclosed by a parentheses ( ) below the individual element's concentration and is based on a Confidence Interval at 95%. Included in this estimated uncertainty, are the combined effects of method imprecision, material inhomogeneity, and any bias between methods.

Important: A "User Registration Card" accompanies all shipments. This card should be completed immediately upon receipt of materials with the appropriate user information. This is the only way in which ARMI can guarantee customer updates or possible data modifications!

Silver 0.005 (0.001)	<u>Aluminum</u> (0.002)	<u>Antimony</u> (0.002)	<u>Arsenic</u>	<u>Beryllium</u>	<b>Bismuth</b>	<u>Carbon</u> (0.01)
Cobalt 0.013 (0.001)	<u>Chromium</u> (0.003)	<b>Copper</b> 87.9 (0.1)	<u>Iron</u> 1.30 (0.01)	Manganese 0.62 (0.01)	Nickel 10.03 (0.06)	Phosphorus 0.004 (0.001)
<u>Lead</u> 0.008 (0.001)	<u>Sulfur</u> 0.008 (0.001)	<u>Selenium</u>	Silicon 0.01 (0.003)	<u>Tin</u> 0.014 (0.002)	Zinc 0.082 (0.004)	

The laboratories participating in the "Inter-Laboratory Analysis Program" (ILAP) and certification of this material are as follows:

Anderson Laboratories, Inc. - Greendale, WI
Bodycote Taussig, Inc. - Skokie, IL
Colonial Metals Co. - Columbia, PA
Crucible Research - Pittsburgh, PA
Laboratory Testing, Inc. - Hatfield, PA
MetalTek International, Inc. - Waukesha, WI
R. Lavin & Sons, Inc. - North Chicago, IL

Bodycote Materials Testing, Inc. - Los Angeles Laboratory Chicago Spectro Service Laboratories - Chicago, IL Consolidated Power Supply - Birmingham, AL I. Schumann & Company - Bedford, OH Lockheed Martin Astronautics - Littleton, CO Outokumpu Research Oy - Pori, Finland Sipi-Metals Corp - Chicago, IL

Traceability: All members of the "Inter-Laboratory Analysis Program" (ILAP) listed above validate test methods and instrument performance utilizing SRMs produced by the National Institute of Standards and Technology, (NIST) as well as other CRMs and RMs produced by recognized Certifying Bodies from around the world. The specific SRMs, CRMs, and RMs applicable to the material covered by this certificate are: NIST 157, 158A, 879, IARM 93A, 94A, BCS 180/2, NIST 1104, C1106, C1107, C1108, C1109, C1110, C1111, C1112, C1113, C1114, C1115, C1116, C1117, C1118, C1119, C1121, 1122, 1123, BNF C51.11, C51.12, C51.13, C51.14, C54.01, C54.02, C54.03, C54.04, C54.05, C54.06, IARM 70A, 71A, 72A, 73A, 74A, 75A, 76A, 77A, 78A, 79A, 80A, 81A, 82A, 83A, 84A, 85A, 86A, 87A, 88A, 89A, 90A, 91A, 92A, 93A, 94A, NIST 124D, 1240, BS706, TASN-100, TBIN-250, TSBH-100, TSNH-500, IARM 83A, LECO 502-148, BCS 304, CTIF CA-27, BAM 211, NIST 1275, MBH CN10, NIST 131F, IARM 84A, IARM 70A, 71A, 73A, 74A, 80A, AR 148, LECO 501-673, 501-675, NIST 62B, 62C, 164A, BS 706A,NIST 1275, IARM 84a, BS 706, Merck 9967, 3819, 9947, 9929, 9953, 9949, Pure Metals Ag-99.95, Cu-99.995, Mn-99.95, Ni-99.9, Pb-99.9, Cd-99.9, Reagecon AACOH, NIST 124D, 37E, BCS 179/2, NIST 875, LECO 501-550, 502-148

A specific line of traceability is established to NIST and other Certifying Bodies for those elements that are noted as "Certified Values" on the Certificates of Analyses referenced above.

See Reverse Side for Statistical Data and Additional Information Regarding this Material.

The following data and accompanying statements represent all pertinent information reported in the ILAP as it applies to the chemical characterization of this material as of 06/15/2004.

84B	Ag	Al	As	Be	Bi	С	Co	Cr	Cu	Fe	Mn	Ni	P	Pb	S
1	0.005	0.0011	< 0.001	0.0012	< 0.0001	0.017	0.011	0.005	87.85	1.29	0.62	10.10	0.004	0.010	0.010
2	0.0063	0.001	0.0001	< 0.001	0.0004	0.0053	0.014	0.0033	87.89	1.31	0.649	10.13	0.003	0.009	0.010
3	0.0035	0.002	0.030	0.0001	< 0.001	0.0125	0.0129	0.003	87.84	1.311	0.62	9.98	0.0022	0.004	0.007
4	0.007	0.0031	< 0.001	0.0001	0.003	0.010	0.010	0.003	87.81	1.322	0.5876	10.123	0.006	0.008	0.0084
5	0.004	0.0025	0.005	< 0.003	0.003	0.0030	0.012	0.0015	88.084	1.28	0.624	9.932	0.006	0.0113	0.009
6	0.0055		0.0002		0.00006	0.006	0.010		88.0	1.29	0.59	10.00	0.005	0.007	0.009
7	0.0063		0.0004		0.0008	0.0044	0.012		87.93	1.31	0.62	9.98	0.0047	0.005	0.0086
8	0.0059		< 0.0010			0.0109	0.017			1.316	0.621	10.07	0.005	0.008	0.007
9						0.0036	0.0155			1.27	0.620	9.848		0.008	0.0097
10							0.0128			1.295	0.612	10.13		0.007	0.0064
11							0.012			1.30	0.6267	10.02		0.0081	0.0072
12										1.28	0.62	10.05		0.008	0.008
13										1.27	0.59			0.010	
14											0.61			0.008	
Mean	0.0054	0.0019	0.0071	0.0005	0.0015	0.0081	0.0127	0.0032	87.9149	1.2957	0.6150	10.0303	0.0045	0.0080	0.0084
STDV.	0.0012	0.0009	0.0129	0.0006	0.0014	0.0048	0.0022	0.0012	0.0979	0.0174	0.0166	0.0875	0.0014	0.0019	0.0012
Certified	0.005	(0.002)				(0.01)	0.013	(0.003)	87.9	1.30	0.62	10.03	0.004	0.008	0.008
95% C.I.	0.001						0.001		0.1	0.01	0.01	0.06	0.001	0.001	0.001
Methods	X,D,I	D,I,O				C,O	X,D,A,I,O	D,I	W,I,O	X,A,I,O	X,A,I,O	X,W,A,I,O	X,I,O	X,A,I,O	X,C,O

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G=GDMS 84B Sb Si Sn Zn Cd Mg Mo 0 Zr Ti Nb 0.0003 0.0005 0.01 0.010 0.070 0.0006 0.0012 0.0003 0.000 0.0008 0.014 0.001 0.002 0.01 0.012 0.080 0.001 0.0056 < 0.003 0.0017 < 0.003 < 0.01 0.0059 0.007 0.0004 0.003 0.010 0.085 < 0.00 < 0.003 4 0.001 0.005 0.0126 0.075 < 0.0010 0.007 < 0.003 0.0004 0.01 0.014 0.0857 0.006 < 0.0010 0.020 0.070 0.020 0.090 8 0.014 0.076 10 0.013 0.085 11 0.0139'0.0815 0.015 0.0886 12 0.087 14 0.085 15 0.089 Mean 0.0014 0.0078 0.0140 0.0819 0.0008 0.0084 0.0010 0.0012 0.0004 0.0010 0.0001 0.0008 STDV 0.0011 0.0024 0.0032 0.0066 0.0003 0.0038 0.0001 0.0010 Certified (0.002)0.01 0.014 0.082 (0.008)95% C.I. 0.003 0.002 0.004

Methods: W = Classical, C = Combustion, F = Fusion, A = AA or GFAA, I = ICP or DCP, D = DC Arc, O = OE, X = XRF, G=GDMS

The International Standards Organization (ISO) definitions, expressed in ISO Guide 30-1981-(E) list the following:

X,D,A,I,O

X,A,I,O

<u>Certifying Body:</u> A technically competent body (organization or firm, public or private) that issues a Reference Material Certificate. The only generally accepted certifying body in the United States is the U. S. Department of Commerce, National Institute of Standards & Technology, (NIST), Gaithersburg, MD.

**Reference Material (RM):** A material or substance with one or more properties which are sufficiently well established to be used for calibration of an apparatus, the assessment of a measurement method, or for assigning values to materials.

<u>Certified Reference Material (CRM):</u> A reference material with one or more properties whose values are certified by a technically valid procedure accompanied by or traceable to a certificate or other documentation, which is issued by a Certifying Body.

<u>Inter-Laboratory Analysis Program (ILAP):</u> Although ASTM Standard E691-87 applies to inter-laboratory studies to "Determine the Precision of a Single Test Method", it is also a well thought out and logical plan for conducting an inter-laboratory program involving multiple techniques. Therefore, the planning, conducting, analyzing, protocol, and treatment of data resulting from this inter-laboratory program were performed utilizing the guidelines established in ASTM E691-87.

<u>Methods of Analysis:</u> In view of the fact, that the "Inter-Laboratory Analysis Program" entails a wide variety of materials, no single analytical method would provide optimum data results. Therefore, the methods utilized were a combination of ASTM Standard Methods for classical wet chemistry, ICP, AA, Optical Emission and X-Ray spectrometric methods. The determinations for Carbon, Sulfur, Nitrogen, and Oxygen are the result of combustion instrument procedures.

Selection of Materials: A "batch" or "series" is defined as a single bar of one continuous length. The majority of materials are in wrought condition. Other methods of manufacture are utilized as a last resort, only in the case of those materials being unavailable in wrought condition. "Batch" samples are taken by removing a one-inch cross section for every thirteen inches of total length from the entire bar. Twenty-five percent of the one inch cross section is converted to chips for analysis by classical wet chemistry, ICP, AA, and combustion procedures and seventy-five percent remains in a solid disk form for OES and X-Ray analysis where applicable. Each member of the ILAP is furnished both a solid sample and the corresponding supply of chips from a specific location on the batch bar. This massive sampling procedure results in the homogeneity being reflected as a product of the overall statistics and certified data.

Certified by:

Methods

William D. Britt, President & General Manager Analytical Reference Materials International Corporation Certificate No.: 84B-03191999-ARM-F Certification Date: 03/19/1999

Revision Date/No.: 06/15/2004